Check for updates

RESEARCH ARTICLE OPEN ACCESS

An Analogue Memristor Based on Conjugated Porous Polymer Composite for Artificial Synapse

Haotian Hao[1] | Xiong Jiao[1] | Guangdong Zhou[2] | Lin Chen[3] | Mixue Wang[4] | Jintao He[3] | Xiaochen Lang[3] | Jiyun Zhang[5] | Linlin Shi[6] | Meiwen An[1] | Lingpeng Yan[3,7] | Yizhi Zhu[6] | Yongzhen Yang[3]

[1]Department of Biomedical Engineering, College of Artificial Intelligence, Taiyuan University of Technology, Taiyuan, China | [2]College of Artificial Intelligence, Chongqing Key Laboratory of Brain-inspired Computing and Intelligent Chips, MOE Key Laboratory of Luminescence Analysis and Molecular Sensors, Southwest University, Chongqing, China | [3]Key Laboratory of Interface Science and Engineering in Advanced Materials, Ministry of Education, Taiyuan University of Technology, Taiyuan, China | [4]Academy of Medical Sciences, Shanxi Medical University, Taiyuan, China | [5]Faculty of Engineering, Department of Material Science, Friedrich-Alexander-University Erlangen-Nuremberg, Institute of Materials for Electronics and Energy Technology, Erlangen, Germany | [6]College of Physics and Optoelectronics, Shanxi Key Lab of Photovoltaic Technology and Application, Key Lab of Advanced Transducers and Intelligent Control System Ministry of Education, Taiyuan University of Technology, Taiyuan, China | [7]College of Materials Science and Engineering, Taiyuan University of Technology, Taiyuan, China

Correspondence: Meiwen An (anmeiwen@tyut.edu.cn) | Lingpeng Yan (yanlingpeng@tyut.edu.cn) | Yizhi Zhu (zmxzzhu@163.com) | Yongzhen Yang (yangyongzhen@tyut.edu.cn)

Received: 2 May 2025 | **Revised:** 4 September 2025 | **Accepted:** 31 December 2025

Keywords: artificial synapse | carbon dot | conjugated porous polymer | memristor | neural interface | neuromorphic computing

ABSTRACT

Artificial synapses have emerged as a pivotal technological advancement in mimicking brain functions. Organic memristors are desirable for hardware implementation of artificial synapses, owing to their remarkable mechanical flexibility, high biocompatibility at cell-device interfaces, and adjustable material structure. Developing appropriate organic polymers with carbon dots modification will enable the memristor to possess analog-type resistive switching behavior, crucial for realizing brain-like associative learning and adapting dynamic variations of neuron connection strength. In this work, an artificial synapse based on the analogue organic memristor integrating neuromorphic computing and neural interface functions is proposed, utilizing synthetic conjugated porous polymers to construct composites with boron-doped carbon dots. The structure-property relationship of alkynyl and alkyl chains in polymers is elucidated, alongside the synergistic effect of local photoinduced redox and hole templating in composites that endows the device with analog-type resistive switching behavior. Moreover, the memristor presents impressive synaptic plasticity and associative memory learning potential for neuromorphic computing, and further serves as a core unit in flexible artificial neural interface chips, demonstrating dynamic information transmission with neural systems. This study will promote the further development of organic artificial synapses for neuromorphic computing and brain-machine interfaces.

1 | Introduction

Artificial synapse, as a pivotal technological pathway for mimicking the human brain, has emerged as a core issue driving the advancement of intelligent computing and interaction systems to higher levels [1–4]. The objective of the artificial synapse is to emulate human brain functions for realizing intelligent computing characterized with large-scale parallelism, high energy efficiency, and exceptional cognitive ability [5, 6]. Another even more encouraging prospect is neural interfaces capable of direct communication with biological systems, given the similarities of neural architecture and functionality between

This is an open access article under the terms of the Creative Commons Attribution License, which permits use, distribution and reproduction in any medium, provided the original work is properly cited.

© 2026 The Author(s). *Exploration* published by Henan University and John Wiley & Sons Australia, Ltd.

the artificial synapse and neural synapse. The neural interface would provide information output channels for brain-like neural computing, complete information exchange and establish an efficient human-computer interaction between the biological neural system and external devices [7].

Memristors have the promising potential to implement such an artificial synapse that integrates neuromorphic computing and neural interfaces [8, 9]. The functional layer material in the middle of memristors provides dynamic interactions with external environment through the reception and response to external stimuli, achieving memory information and training [10–14]. Organics are encouraging for neuromorphic electronics due to remarkable mechanical flexibility/stretchability, biocompatibility with cell-device interfaces, and tunable molecular structure [15, 16]. In general, organic memristor exhibits digital-type resistive switching (DRS) behavior, enabling abrupt transitions between high and low resistive states (HRS/LRS), representing information writing and erasing via formation and rupture of conductive filaments (CFs) [17]. In addition to DRS, analog-type resistive switching (ARS) behavior holds considerable potential for memristor-based artificial synapses. ARS possesses the characteristic of gradually tunable conductance [18–20], mimicking the constantly changing behavior of neurons connection strength in biological systems, and thus offers performance benefits in simulating brain computing and adapting to dynamic variations of neural interface connections. By designing and optimizing the structure of organic materials, the conduction mode of memristors can be modulated to achieve ARS behavior.

In this context, conjugated porous polymers (CPPs), characterized by inherent porosity and extended π-conjugated electronic system [21–23], emerging as a promising material for memristors. The porous channel structure has been verified to possess a hole template effect for the ordered growth of CFs, contributing to improving device uniformity [24]. The long-range π-conjugated structure of CPPs enables electrons to transfer over a wide range [25], which is conducive to reduce power consumption. Through precisely manipulating the chemical bonds and functional groups, the migration of electrons and ions can be modulated in the memristor, directly influencing memristor performance. Furthermore, the strategy of carbon dots (CDs) doping CPPs will support developing ARS-type memristors. Our recent work has proved that boron-doped CDs (BCDs) can significantly enhance device stability, primarily attributed to the capability of effectively capturing free electrons and subsequently inducing ordered CFs formation [26]. CDs can effectively adhere to CPPs characterized by a large specific surface area, and the local chemical environment of CPPs can be modulated by CDs. This potentially achieves ARS behavior for memristor through inducing the formation of weak CFs [20]. Therefore, employing the composite of CPPs and CDs is anticipated to expedite the progress of an artificial synapse based on organic memristor.

Herein, an artificial synapse based on the organic memristor is proposed (Figure 1), integrating brain-like neuromorphic computing and neural interface functions. Three structurally similar triazine-based CPPs are synthesized and utilized to construct the composite with BCDs (BCDs@CPPs), which is then used to fabricate a memristor exhibiting ARS behavior. The role of alkynyl and alkyl chain on memristance is systematically investigated through an analysis of CPPs structure and device performance. Considering the movement of photogenerated electrons, it can be judged that weak CFs induced by local redox reaction determine device performance. The composite-based memristor exhibits promising neuromorphic computing capabilities by demonstrating synaptic plasticity and associative memory learning potential, effectively simulating biological neural network information processing. On this basis, this capability is further extended to neural interfaces, showing potential in biological signal transmission. The memristor is incorporated into a flexible artificial neural interface chip (ANIC), which responds to secretions from neuronal PC12 cells triggered by the release of dopamine (DA) through a heat-responsive polyvinyl alcohol (PVA) hydrogel. This achieves effective neurotransmitter signaling in a loop between neural interface and biological neural system.

2 | Results and Discussions

2.1 | The Synthesis and Structure-Property Relationship of CPPs

The structure of three triazine-based CPPs is designed in Figure 2A. Triphenyltriazine, as a key repeating node unit, is connected to form structurally similar CPP1, CPP2, and CPP3 through fluorene, alkynyl, and alkynyl fluorene, respectively. The triazine unit, serving as an electron-withdrawing moiety [27], is capable of forming a donor–acceptor (D-A) polymer with fluorene group, thereby enhancing electron transfer along the polymer backbone. Upon excitation by ultraviolet, the triazine unit typically facilitates the separation of electron–hole pairs and initiates redox reactions in situ [28, 29], generating photogenerated electrons that may modulate the memristance property. The alkynyl group, acting as the π-bridge in D-A polymers, can enhance the intramolecular charge transfer and adjust channel aperture size. The alkyl chains of D-A polymers can prevent aggregation, thereby endowing the polymers with solution-processability. These CPPs were synthesized using Sonogashria, Eglinton, and Suzuki coupling methods, and the synthesis routes are shown in Figures S1 and S2. The nuclear magnetic resonance spectra provide evidence for synthetic intermediate compounds C1–C6 (Figures S3–S8), and the Fourier transform infrared (FTIR) spectra analysis also proves the successful synthesis of CPPs (Figure S9). The stretch vibration absorption peaks of C≡C in C3 and C4 are located at 2156 and 2106 cm^{-1}, respectively. C4 exhibits the C—H signal of alkynyl at 3298 cm^{-1}, which indicates that C3 successfully transforms into C4 after removing the trimethylsilyl protecting group. Compared to the C≡C peak of C5 (2158 cm^{-1}), the signal of that in CPP1 (2190 cm^{-1}) shows a red-shift, which is attributed to CPP1 itself having a greater conjugated degree. The C—B (961 cm^{-1}) and C—O (1144 cm^{-1}) stretching vibration peaks, originally present in C2, are absent in the CPP2 spectrum, which corresponds to the bond cleavage at the reaction site during synthesis process of CPP2. In further analysis, it is evident that the C≡C signal presents in C4 (2106 cm^{-1}) and CPP3 (2193 cm^{-1}), whereas alkynyl hydrogen (3298 cm^{-1}) is exclusively observed in C4, suggesting C4 reacts with T1 to yield CPP3. In the FTIR spectra of CPPs (Figure 2B), the bands (I) and (II) illustrate that the C—H bond of alkyl chain appears in CPP2 and CPP3, while the C≡C groups exist in CPP1 and CPP3. The peaks in bands (III)–(V) correspond to

27662098, 2026, 1, Downloaded from https://onlinelibrary.wiley.com/doi/10.1002/EXP.20250234 by CochraneChina, Wiley Online Library on [08/06/2026]. See the Terms and Conditions (https://onlinelibrary.wiley.com/terms-and-conditions) on Wiley Online Library for rules of use; OA articles are governed by the applicable Creative Commons License




FIGURE 1 | Schematic diagram of the organic composite (BCDs@CPPs) and the memristor for artificial synapse. (A) The preparation process of CPPs, BCDs@CPPs composite, and memristor. (B) Memristance property and working mechanism. (C) Schematic diagram of the brain-like device used for artificial synapse.

the triazine group, out-of-plane and in-plane bending vibration peaks of C—H in turn. According to XRD patterns (Figure 2C), all CPPs have relatively wide diffraction peaks in the range of 20°–25°, indicating that they all possess amorphous structures. The BET measurement (Figure S10) indicates that the surface areas of CPP2 (171 $cm^2\ g^{-1}$) and CPP3 (198 $cm^2\ g^{-1}$) are larger than that of CPP1 (47 $cm^2\ g^{-1}$), which may be due to the presence of alkyl chains that prevent the accumulation of CPP2 and CPP3, thus exposing larger surface area. The average pore diameters of CPP1, CPP2, and CPP3 increase sequentially, which is consistent with the trend of theoretically increasing pore sizes for three CPPs. Moreover, the thermogravimetric analysis (TGA) reveals an obvious weight loss in CPPs within 400–600°C (Figure 2D), which is attributed to the thermal decomposition of triazine moiety and alkyl chain [30, 31]. Notably, CPPs exhibit very little weight loss before 300°C, indicating CPPs have good thermal stability in normal environments, which is advantageous for memristor stability.

27662098, 2026, 1, Downloaded from https://onlinelibrary.wiley.com/doi/10.1002/EXP.20250234 by CochraneChina, Wiley Online Library on [08/06/2026]. See the Terms and Conditions (https://onlinelibrary.wiley.com/terms-and-conditions) on Wiley Online Library for rules of use; OA articles are governed by the applicable Creative Commons License




FIGURE 2 | The structure-property relationship between CPPs and memristor performance. (A) Schematic diagram of theoretical structure units of CPPs. (B) FTIR spectra, (C) XRD pattern, and (D) TGA of CPPs. *I–V* curves of the memristors based on (E) CPP1, (F) CPP2, and (G) CPP3. The CAFM current images (3×3 μm) of (H) CPP1, (I) CPP2, and (J) CPP3 film after a SET stimulus (4 V). (K) Comparative analysis of CFs and CPPs structure to reveal structure-property relationship between CPPs and memristor performance.

27662098, 2026, 1, Downloaded from https://onlinelibrary.wiley.com/doi/10.1002/EXP.20250234 by CochraneChina, Wiley Online Library on [08/06/2026]. See the Terms and Conditions (https://onlinelibrary.wiley.com/terms-and-conditions) on Wiley Online Library for rules of use; OA articles are governed by the applicable Creative Commons License

The powdery CPPs exhibit limited solubility in solvents, hampering the efficient preparation of functional layer films. Therefore, it is imperative to achieve the uniform dispersion of poorly soluble CPPs in solvents for obtaining solution processability. CPPs chloroform solution is prepared by sonication (Figure S11), and the morphology of CPPs before and after ultrasonic treatment is shown in Figure S12. From the transmission electron microscope (TEM) images before ultrasonication, CPP1 exhibits a stacked morphology, while CPP2 and CPP3 are spheroidal. The morphological difference between CPPs is primarily attributed to the alkyl chains that tend to occupy the cavity of polymers, resulting in spheroidal CPP2 and CPP3 [30]. After ultrasonication, all CPPs manifest layered structure. The observed local lattice fringes indicate a more ordered structure. Ultrasonication can disperse the stacked CPP1 and effectively unfurl the alkyl chains of CPP2 and CPP3 from the cavity of polymers, which transforms CPPs into a layered morphology, resulting in increased surface area and composite sites.

The CPPs-based memristor presents an Al/CPPs/ITO/glass structure, in which the CPPs layer possesses a relatively smooth morphology in a 5×5 μm area (Figure S13). The memristor based on CPP1 is activated at +1.45 V (Sweep1) and then sustains at LRS throughout subsequent scans with both positive and negative electric fields (Sweep2–Sweep5), as shown in Figure 2E. Even exerting a +4 V bias voltage after a 15 min power interruption, the CPP1-based memristor still remains at LRS (Sweep6), which aligns with the write-once-read-many times (WORM) characteristic. The CPP2-based memristor exhibits ARS behavior with gradually adjustable resistance state after the first forming cycle that corresponds to CFs generation, and can then be reliably cycled in positive and negative electric fields (Figure 2F). The CPP3-based memristor performs SET operation at +1.70 V (Sweep1), exhibiting similar memristive characteristics to the CPP1-based memristor before power interruption (Sweep2–Sweep5), as shown in Figure 2G. However, after a 15 min power interruption, the device returns to HRS voluntarily, manifesting the volatility of data. Once reapplying a +4 V bias voltage, the device performs a writing operation again (Sweep6). These features demonstrate that the CPP3-based memristor presents a static random-access memory (SRAM) behavior [32].

The resistive switching behaviors of three CPPs-based memristors are closely associated with their respective CFs. The CFs of the CPP1-based memristor exhibit high strength and difficult disruption, as evidenced by the device keeping at LRS during both positive and negative electric field scans, as well as upon re-stimulation after power interruption. The device performance of CPP3-based memristor is similar to that of CPP1-based memristor before power interruption, but a SET operation is required in the subsequent operation, indicating that the CFs within film also have relatively high strength. However, the disconnection after power interruption indicates that the strength of the CFs in CPP3 film is inferior to that in CPP1 film. The current of CPP2-based memristor is uninterrupted variation, which illustrates that the CFs within CPP2 film are sensitive to continuous changes of electric fields, thereby indicating these CFs exhibit weak strength. These CFs of distinct CPPs films can also be observed from their conductive atomic force microscopy (CAFM) current images (Figures 2H–J). CPP1 film exhibits strong current paths, whereas the current paths of CPP2 film appear to be extremely weak, and current intensity of CPP3 falls between CPP1 and CPP2. The specific structure of CPPs is related to the CFs property (Figure 2K). Alkyl chain is absent in CPP1, whereas this group presents in both CPP2 and CPP3. Thus, it is inferred that alkyl chain may physically intervene in the growth of CFs, resulting in the inferior strength of CFs in CPP2 and CPP3 compared to that of CPP1. Similarly, alkyne groups contribute to the formation of more stable CFs in CPP1 and CPP3. The CFs are less likely to dissolve or rupture even under the reverse electric field, enabling CPP1 and CPP3 to maintain LRS. This molecular-level design provides a foundational strategy for tailoring organic memristors with specific memristor performance.

2.2 | The Composite-Based Memristor and Working Mechanism

The current range of CPP2-based memristor is significantly lower than that of CPP1- and CPP3-based memristors, thus meeting the low-power requirements of artificial synapses. The selected BCDs can enhance memristance property effectively and have been synthesized in our previous work [26]. The ability of this polymer/inorganic hybrid system to effectively regulate electron movement has been explored in other fields [33–38]. The schematic diagram of BCDs@CPP2 composite is depicted in Figure 3A. BCDs can associate well with layered CPP2 in chloroform to form the composite (Figure 3B), and their lattice fringes are clearly visible in high-resolution TEM (HRTEM) image (Figure 3C). By analyzing the contour intensity of the lattice fringes in the inverse fast Fourier transform (IFFT) image (Figure 3D), it can be determined the average crystal plane spacing is approximately 0.212 nm (Figure 3E), which is close to that of BCDs (0.213 nm) [26], indicating BCDs are successfully attached to CPP2. The surface topography of composite film (5×5 μm) was measured using atomic force microscopy (AFM) (Figure 3H), revealing a root-mean-square (RMS) value of only 0.078 nm, which is significantly lower than that (5.52 nm) of CPP2 film (Figure S13E). This indicates that the insertion of BCDs into CPP2 reduces the disordered stacking morphology of CPP2 and decreases surface roughness of the CPP2 film, resulting in a smoother film that is conducive to promoting electron transport. Moreover, the functional layer is mainly stacked by BCDs@CPP2 composite that presents layered morphology. The marked blue line in the AFM image spans four layers of composite films, and the corresponding contour line chart shows that the thickness of each layered film is between 1–2 nm. This kind of ultra-thin layered composite is expected to shrink the device size, and may obtain other advantages of high carrier mobility, stable switching behavior, and controllable neuromorphic characteristics [39, 40].

The *I–V* curve of BCDs@CPP2-based memristor (Figure S14A) exhibits DRS with a small memory window. After illuminating the device from bottom for 20 min by ultraviolet irradiation, the device presents the gradual and continuous ARS behavior with an expanded memory window (Figure 4A), indicating a transition from DRS to ARS. Besides, the photosensitive device demonstrates that conductance gradually decreases under a negative electric field (i.e. inhibitory behavior) and increases under a positive electric field (i.e. potentiation behavior), as shown in Figure 4C,D. The above performances indicate that

27662098, 2026, 1, Downloaded from https://onlinelibrary.wiley.com/doi/10.1002/EXP.20250234 by CochraneChina, Wiley Online Library on [08/06/2026]. See the Terms and Conditions (https://onlinelibrary.wiley.com/terms-and-conditions) on Wiley Online Library for rules of use; OA articles are governed by the applicable Creative Commons License




FIGURE 3 | Morphology of the composite and its memristor device. (A) Schematic diagram of CPP2 and its composite with BCDs. (B) TEM and (C) HRTEM images of the composite, and the area in the white framework is transferred into (D) the IFFT pattern, showing a typical HRTEM image of the individual BCD with a crystal plane spacing of 0.212 nm. (E) Profile of IFFT along the yellow line in Figure D). (F) Schematic diagram of the composite-based memristor. (G) Cold field emission scanning electron microscopy image of the device cross-section, arranged from bottom to top with a glass substrate, bottom ITO electrode (100 nm), BCDs@CPP2 functional layer (125 nm), and top Al electrode (70 nm). (H) The AFM image of composite film, and the line profile of four-layered films along the blue line.

the composite-based memristor meets the criteria for being a candidate device for constructing artificial synapses [41].

The ARS behavior is closely related to photogenerated carriers, which can be elucidated through transient photovoltage (TPV) of CPP2 and its BCDs@CPP2 composite. Initially, the TPV value of CPP2 is negative before 0.047 ms (Figure 4E), indicating the generation and accumulation of photogenerated electrons on its surface under ultraviolet excitation [42]. Subsequently, these electrons are consumed by oxygen due to oxidation, leading to an accumulation of photogenerated holes on CPP2 surface and causing positive TPV. While the TPV of composite maintains positive throughout and gradually decayed to 0 over time (Figure 4F). Specifically, the BCDs can capture the photogenerated electrons produced by CPP2 under ultraviolet excitation due to their strong electron trapping ability. Consequently, the photogenerated holes keep a positive TPV for composite. The gradual decrease of TPV value to 0 is attributed to the recombination of photogenerated electrons and holes or other relaxation [42]. In short, a local photoinduced redox occurs between CPP2 and BCDs.

A model of photoinduced weak CFs is proposed to explicate the ARS behavior of composite-based memristor (Figure 4G), taking into account the material structure, device performance, and TPV analysis. In the absence of ultraviolet stimulation, similar to the BCDs-based memristor [26], the composite-based memristor exhibits multilevel resistive switching behavior (Figure S14A). While upon ultraviolet excitation, a local photoinduced redox occurs between CPP2 and BCDs, leading to the separation of holes and electrons. Such photogenerated carriers can be efficiently separated and transported within CPP2, attributing to the alternating distribution of positive and negative potential regions, supported by molecular simulation based on density functional theory (Figure S15). Based on the TPV result and

27662098, 2026, 1, Downloaded from https://onlinelibrary.wiley.com/doi/10.1002/EXP.20250234 by CochraneChina, Wiley Online Library on [08/06/2026]. See the Terms and Conditions (https://onlinelibrary.wiley.com/terms-and-conditions) on Wiley Online Library for rules of use; OA articles are governed by the applicable Creative Commons License




FIGURE 4 | Performance and mechanism of the composite-based memristor. Cyclic *I–V* curves of device (A) with and (B) without ultraviolet treatment. *I–V* curves under consecutive (C) negative and (D) positive voltage sweeps after ultraviolet treatment. The TPV curve of (E) CPP2 and (F) composite at 355 nm. (G) Schematic diagram of photogenerated electron-induced weak CFs mechanism under ultraviolet irradiation.

the trapping electron ability of BCDs, it is evident that the holes accumulate on CPP2 surface, while the photogenerated electrons are strongly attracted towards and localized at the BCDs sites. These localized electrons create a reducing environment around the BCDs, facilitating the reduction of mobile Al^{3+} (originating from the top electrode under bias) to metallic Al atoms. This reduction process nucleates the formation of metallic CFs primarily at or between adjacent BCDs sites. In addition, the simulated calculation reveals that CFs are typically formed between adjacent BCDs and present interconnectedness (Figure S16). Under reverse bias, CFs undergo electrochemical oxidation, dissolving partially as Al^{3+} ions, and the current declines. Such weak and interconnected CFs in porous composite gradually form or disconnect in response to voltage variations, enabling the device to exhibit repeatable and cyclic ARS behavior. This composite design with the synergistic effect of local photoinduced redox and hole templating provides a promising approach for constructing ARS-type memristors, which enables gradual conductance modulation essential for artificial synapses.

2.3 | Analogue Memristor for Neuromorphic Computing and Neural Interface

In neural synapses, as an important component in neural conduction, excitatory post-synaptic current (EPSC) can facilitate the transmission of synaptic excitation signals to induce neuronal excitation, consequently causing action potentials. Given the similarity in structure and operational mechanism between memristor and neural synapse (Figure 5A) [43], it is imperative to investigate EPSC. Current response of the ARS-type memristor can be triggered under a single pulse (4 V, 50 μs), and gradually decays after removing stimulus (Figure 5B), suggesting an obvious EPSC characteristic. In contrast, the device without ultraviolet irradiation fails to display a significant EPSC

27662098, 2026, 1, Downloaded from https://onlinelibrary.wiley.com/doi/10.1002/EXP.20250234 by CochraneChina, Wiley Online Library on [08/06/2026]. See the Terms and Conditions (https://onlinelibrary.wiley.com/terms-and-conditions) on Wiley Online Library for rules of use; OA articles are governed by the applicable Creative Commons License




FIGURE 5 | Synaptic learning functions emulated by the composite-based memristor. (A) Schematic diagram of the relationship between the neural synapse and memristor. (B) EPSC of BCDs@CPP2-based memristors treated by ultraviolet light for 20 min. (C) PPF index and the fitted curve of the device triggered by paired spikes with different interval times. The transition from STP to LTP by regulating (D) the stimulus pulse amplitude and (E) frequency. (F) Relative changes of the synaptic weight with interval time, showing a typical STDP function. (G) Simulation of multiple learning and forgetting behaviors of the human brain. (H) Simulation of Pavlov's dog experiment: bell ringing stimulus (0.1 V pulses), food stimulus (4.0 V pulses), the combined training sequence with the bell and food (a 4.0 V pulse followed by a 0.1 V pulse), and bell ringing stimulus (0.1 V pulses). V_{read} is 1.0 V.

27662098, 2026, 1, Downloaded from https://onlinelibrary.wiley.com/doi/10.1002/EXP.20250234 by CochraneChina, Wiley Online Library on [08/06/2026]. See the Terms and Conditions (https://onlinelibrary.wiley.com/terms-and-conditions) on Wiley Online Library for rules of use; OA articles are governed by the applicable Creative Commons License

response. The paired-pulse facilitation (PPF) function represents the temporal correlation between adjacent spikes [44], and is associated with Ca^{2+} biological dynamics [45]. PPF is simulated by two successive pulses (4 V, 50 μs), and shows that the second spike is higher than that of the first spike. PPF index can be calculated and fitted by the following equations:

$$\text{PPF ratio} = A_2/A_1 \quad (1)$$

$$\text{PPF index} = 1 + C_1 \exp(-\Delta t/\tau_1) + C_2 \exp(-\Delta t/\tau_2) \quad (2)$$

where A_1 and A_2 are the first and second EPSC peaks, C_1 and C_2 denote the initial magnitudes of facilitation, Δt is interval time, τ_1 and τ_2 represent relaxation times. The decreased interval time between spikes is directly correlated with the enhanced PPF index (Figure 5C), signifying an increased susceptibility of the device to facilitation [46, 47]. Both EPSC and PPF behaviors belong to short-term plasticity (STP), which is essential for artificial synapses to perform the neuromorphic computing [44, 48].

Long-term plasticity (LTP) is also crucial to the learning and memory storage of nervous system. Repeated rehearsal events can significantly alter the synaptic weight (ΔG), enabling a transition from STP to LTP. The electrical pulses with varying amplitudes (2.0, 2.5, 3.0, 3.5, and 4.0 V) were applied to the memristor (Figure 5D), revealing that higher voltages promote an increase in memory retention, and gradually manifesting LTP, which indicates a stimulus-amplitude-dependent plasticity (SADP) [48]. Similarly, when pulse frequency increases from 3.33 to 10.0 kHz, memory retention also enhances (Figure 5E), corresponding to the stimulus-frequency-dependent plasticity (SFDP) [48]. The conductance ratio (G_{max}/G_{min}) shows the apparent variation of EPSC with the adjustment in pulse amplitude and frequency (Figure S18B,C). The device is mimicked spiking-timing-dependent plasticity (STDP) which is one of the representative behaviors of unsupervised learning in neural networks. STDP can refine and improve the traditional Hebbian synaptic plasticity by adjusting the interval time between the pre- and postsynaptic stimuli, generating long-term potentiation and long-term depression [44, 49]. The pulse sequences with different interval times were applied to the device (Figure S18D,E), and STDP data is shown in Figure 5F. The corresponding fitting curve is derived from the formula (Figure S18F). Specifically, when presynaptic stimulus precedes postsynaptic stimulus, the device exhibits a potentiation behavior, otherwise, it demonstrates an inhibitory behavior. When the interval time decreases, it is more likely to cause conductance changes, similar to the behavior of biological synapses [45]. The realization of STDP indicates BCDs@CPP2-based memristor has a potential to simulate biological learning processes for neuromorphic computing.

The ARS-type memristor demonstrates associative memory learning potential by mimicking the learning and forgetting behavior and Pavlov's dog conditioned reflex experiment. In the learning and memory process, biological synapses in the brain commences with the formation of STP upon receiving stimulus information. The repeated training creates a transition from STP to LTP. Conversely, the information will gradually be forgotten if synaptic training ceases [50]. The learning process of synapse devices can be achieved by a series of stimulus that gradually increase synaptic weights. Correspondingly, the forgetting process is simulated by the gradual decrease of synaptic weights after taking away the stimuli. Herein, the ARS-type memristor is used to simulate a multiple learning and forgetting process (Figure 5G). By continuously applying 20 pulses (4 V, 50 μs) with an interval of 50 μs to the device, the memory intensity (current intensity) gradually increases until reaching its maximum memory intensity, denoted as I_{max}. Removing the pulses, the final memory intensity retains about 15% of I_{max}. Then, the device is subjected to a relearning operation again, and the electrical pulse used is consistent with that used in the initial learning. The memory intensity ultimately reaches 120% of I_{max}, which significantly improves the upper limit of memory intensity. The trace amount of CFs remaining in the device after the previous training can reactivate the device during a relearning process, showing more obvious memory intensity. The final memory intensity retains about 42% of I_{max}, stronger than that of the first forgetting process. In brief, the BCDs@CPP2-based memristor can successfully simulate the memory function of the human brain. Furthermore, the device establishes a connection between the stimulus and response by simulating Pavlov's dog conditioned reflex experiment (Figure 5H), which is crucial for associative memory learning. In Pavlov's dog experiment, bell ring does not elicit salivation, whereas food does. Through the repeated pairing of bell ring and food, the dog associates bell ring with food, developing a conditioned reflex where solely bell ring induces salivation. In this context, bell ringing acts as a conditioned stimulus (CS), food acts as an unconditioned stimulus (US), and salivation is an unconditioned reflex. By applying the training pulse sequence to the device, the corresponding current can be read. An output current of 1 μA is set as the effective threshold for "salivation" reflex. First, when CS signal is applied to device, the output current is approximately 0.5 μA, below the "salivation" threshold, which corresponds to a dog no salivating when hearing a bell ring. Second, when applying US, a postsynaptic current response exceeds 60 μA, indicating the dog's salivation reflex to food. Subsequently, when the device is trained with a composite signal of US and CS, the output current remains above the threshold, illustrating that the dog still salivates under the combined stimuli of bell ring and food. Finally, when only the CS is applied to the synaptic device, an output current above the threshold is also obtained, corresponding to the dog's salivation reflex when receiving the bell ring alone. The simulation of Pavlov's dog conditioned reflex experiment with this device demonstrates its potential in associative memory learning by establishing a connection between stimulus and response, which facilitates neuromorphic computing systems to mimic brain-like learning, resulting in enhanced learning efficiency and adaptability.

The composite-based memristor, as an artificial synapse, successfully mimics the synaptic connections in associative memory learning cases, exhibiting facilitation characteristics in its current during the stimulation and response cycle. When receiving similar stimulation signals, this memristor can recognize and process these signals more accurately and rapidly, which is important for neural interfaces. Consequently, an artificial synapse utilizing such a memristor is further developed for neural interface to realize information transmission (Figure 6A). A flexible ANIC was fabricated on a polyethylene terephthalate (PET) substrate by integrating a memristor array, a heat-triggered DA release

27662098, 2026, 1, Downloaded from https://onlinelibrary.wiley.com/doi/10.1002/EXP.20250234 by CochraneChina, Wiley Online Library on [08/06/2026]. See the Terms and Conditions (https://onlinelibrary.wiley.com/terms-and-conditions) on Wiley Online Library for rules of use; OA articles are governed by the applicable Creative Commons License




FIGURE 6 | Realization of communication between ANIC and neural cells. (A) Schematic diagram of ANIC preparation and transmission implementation between ANIC and PC12 cells. (B) The temperature of PVA hydrogel positioned on the heater, measured while a bias voltage ranging from 0 to 5 V was applied to the composite-based memristor. (C) The released DA concentration in PC12 cells culture dish and the memristor current measured by applying a training pulse sequence (4 V, 1 ms). (D) Cell viability of the ANIC materials including PET (purple), ZIF-8 (orange), PVA hydrogel (blue), and ZIF-8@PVA hydrogel (red), determined by Cell Counting Kit 8 (CCK8). Data are presented as mean values (SD), and error bar was obtained from three independent experiments. (E) Mean fluorescence intensity and (F) fluorescence Ca^{2+} imaging of neural PC12 cells when exposed to released DA for different time. Scale bar: 50 μm.

27662098, 2026, 1, Downloaded from https://onlinelibrary.wiley.com/doi/10.1002/EXP.20250234 by CochraneChina, Wiley Online Library on [08/06/2026]. See the Terms and Conditions (https://onlinelibrary.wiley.com/terms-and-conditions) on Wiley Online Library for rules of use; OA articles are governed by the applicable Creative Commons License

system (DA@ZIF-8@PVA hydrogel), and a polydimethylsiloxane (PDMS) microfluidic film (Figure S19). The memristor in ANIC, connected in series with a heater, is responsible for processing the external electric signals and controlling the DA release system that serves as a model for axon vesicles releasing neurotransmitters. In the DA release system, ZIF-8 is a kind of effective DA carrier with excellent biocompatibility, its structure and morphology have been confirmed correctly by FTIR, XRD, and TEM (Figures S20 and S21). The temperature-response PVA hydrogel was prepared through a cyclic freeze–thaw process, and exhibits temperature sensitivity within a range of human body temperature. This temperature range ensures the integrity of the PVA hydrogel at room temperature while preventing a thermal burn to physiological tissues. When the bias voltage ranging from 0 to 5 V is applied to the memristor, an increase in heater temperature from 36.0 to 43.3°C is observed (Figure 6B), resulting in deformation and melting of the hydrogel (Figure S22). The stimulation of 4 V is sufficient to ensure that the heater reaches a temperature capable of melting the hydrogel. Thus, a training pulse sequence (4 V, 1 ms) was applied to the memristor. As the heater temperature gradually increases, the accumulated Joule heat leads to the breaking of hydrogen bonds and crystallite melting of the PVA hydrogel [51], facilitating the diffusion of DA@ZIF-8 out of the PVA hydrogel. This process mimics the excitation of action potential and release of neurotransmitters from presynaptic neurons. The results reveal that an increase in memristor current is initiated after 50 s, accompanied by a gradual elevation in heater temperature (Figure 6C). The rise in temperature facilitates an increased release of DA from PVA hydrogel. The concentration of DA can be quantifiable using a standard absorption curve (Figure S23B). After training the memristor for 100 s, it is noted that the concentration gradually ascends, with a notable increase in DA release occurring every 50 s. The LTP behavior of the memristor plays a crucial role in this process. Repeated training establishes stronger connections, thereby improving the sensitivity of ANIC to external stimuli. As a result, the DA release behavior exhibits a characteristic like long-term potentiation, which has not been widely reported (Table S1).

ANIC continues to be utilized to trigger neuronal cells for realizing the transmission of neurotransmitters between neural interface and biological system. Through the specific coupling of G proteins with DA receptors, DA can activate signaling pathways, effectively augmenting intracellular calcium release and modulating both neuronal excitability and synapse transmission [4, 52, 53]. Therefore, the triggering effect of ANIC on neuronal cells can be demonstrated through the Ca^{2+} fluorescence imaging technique. PC12 cells were selected to receive transmission signals from ANIC. The cytotoxicity of various materials, including ZIF-8, PVA hydrogel, ZIF-8@PVA hydrogel, and PET, was systematically evaluated using the live/dead cell staining technique and CCK8 assay. The result demonstrates an insignificant number of dead cells in the presence of these materials. When PC12 cells are exposed to these materials for incubation with 6, 12, and 24 h, their viability remains above 95%, thereby affirming acceptable biocompatibility of materials (Figure 6D). During the initial stage of stimulation training on the memristor, the released DA concentration is negligible, resulting in negligible fluorescence intensity. As the pulse continues to train the memristor, the mean fluorescence intensity gradually increases to 54.0 from 3.1 within 400 s (Figure 6E), and the fluorescence intensity of PC12 cells brightens considerably (Figure 6F), illustrating the successful transmission of neurotransmitters from ANIC to PC12 cells. These results demonstrate that the memristor, serving as the core unit of ANIC, enables dynamic neurotransmitter-mediated communication with living neural cells while exhibiting a long-term potentiation characteristic, which directly mimics dynamic variations in neuronal connection strength.

3 | Conclusion

An artificial synapse integrating neuromorphic computing and neural interface functions is proposed, utilizing an ARS-type organic memristor based on BCDs@CPP2 composite. Firstly, CPP1, CPP2, and CPP3 are designed and synthesized, and the corresponding memristors exhibit WORM, ARS, and SRAM behaviors, respectively. The effect of polymer structure on memristance reveals that alkynyl promotes the formation of stronger CFs, while alkyl chain interferes with CFs strength. Subsequently, the organic composite is prepared by physical blending, and its film presents stacked ultrathin layered structures. The composite-based memristor exhibits gradually tunable conductance under ultraviolet irradiation due to weak CFs induced by the synergistic effect of hole template and photoinduced redox. The feasibility of designing a composite with this synergistic effect for organic artificial synapses is thereby established. Moreover, this device displays EPSC, PPF, STP, LTP, STP to LTP transition, and STDP behaviors under electrical pulse training. The composite-based memristor successfully simulates the memory process, showing a 120% increase in memory intensity during relearning and ultimately retaining 42%. It also mimics Pavlov's dog experiment by establishing a connection between stimulus and reflex, highlighting its potential for associative memory learning in neuromorphic computing. These simulations exhibit the memristor's neuromorphic computing capability. Furthermore, this capability is extended to the neural interface, demonstrating potential for biological signal transmission in an ANIC that integrates a composite-based memristor array, DA release system, and PDMS microfluidic film. In the DA release system, heat-trigger PVA hydrogel can release DA that is directed towards neural PC12 cells through a PDMS microfluidic film. This process mimics presynaptic neuron excitation transmission and exhibits enhanced DA release behavior under repeated training that corresponds to the long term potentiation characteristic. The successful transmission from ANIC to PC12 cells confirms its potential for brain-machine interfaces. In conclusion, this work advances organic artificial synapses through three integrated innovations: (i) Molecular design principles of functional groups to control resistive switching modes; (ii) A synergistic effect leveraging photoinduced redox and hole templating for gradual conductance modulation; (iii) A unified device integrating functions of neuromorphic computing and neural interfaces, enabling dynamic bio-communication.

4 | Methods

4.1 | Synthesis of C1

2,7-dibromofluorene (1 g, 3.1 mmol) and tetrabutylammonium chloride (111 mg, 0.4 mmol) were added in a 100 mL flask.

27662098, 2026, 1, Downloaded from https://onlinelibrary.wiley.com/doi/10.1002/EXP.20250234 by CochraneChina, Wiley Online Library on [08/06/2026]. See the Terms and Conditions (https://onlinelibrary.wiley.com/terms-and-conditions) on Wiley Online Library for rules of use; OA articles are governed by the applicable Creative Commons License

Then under the protection of N_2, dimethyl sulfoxide (5 mL) and 50% aqueous NaOH (5 mL) were sequentially added. After 30 min, 1-bromohexane (1.3 g, 8 mmol) was added. After reacting at room temperature for 12 h, the reaction mixture was added dichloromethane, and the organic phase was washed with a saturated solution of NaCl and then dried from anhydrous magnesium sulfate. The crude product was collected by a vacuum rotary evaporator and purified by silica gel column chromatography to obtain the desired product as a white powder (1.18 g, 86%). ^{1}H NMR (400 MHz, Chloroform-d) δ (ppm): 7.52 (d, J = 8.0 Hz, 2H), 7.45 (dd, J = 7.8, 1.6 Hz, 4H), 1.94–1.88 (m, 4H), 1.14–1.02 (m, 12H), 0.78 (td, J = 7.2, 1.4 Hz, 6H), 0.57 (dd, J = 10.3, 5.9 Hz, 4H).

4.2 | Synthesis of C2

Under the protection of N_2, *n*-butyllithium (2.5 M, 2.4 mL, 6 mmol) was added dropwise to the distilled tetrahydrofuran (25 mL) containing C1 (985 mg, 2 mmol) at −78°C. The resulting solution was stirred for 1 h and was then added isopropoxyboronic acid pinacol ester (1.96 mL, 9.6 mmol). The reaction was gradually raised to room temperature and stirred overnight. Then dichloromethane was added, and the organic phase was washed with a saturated solution of NaCl. The crude product was collected by a vacuum rotary evaporator and purified by silica gel column chromatography to obtain the desired product as a white powder (540 mg, 46%). ^{1}H NMR (400 MHz, Chloroform-d) δ (ppm): 7.83 (d, J = 7.6 Hz, 2H), 7.77 (s, 2H), 7.74 (d, J = 7.6 Hz, 2H), 2.06–1.98 (m, 4H), 1.41 (s, 24H), 1.13–0.99 (m, 12H), 0.76 (t, J = 7.1 Hz, 6H), 0.61–0.52 (m, 4H).

4.3 | Synthesis of C3

Under the protection of N_2, a mixture of C1 (985 mg, 2 mmol) in freshly distilled diisopropylamine (20 mL) solution was added CuI (19 mg, 0.1 mmol) and $Pd(PPh_3)_2Cl_2$ (70 mg, 0.1 mmol). After the solution was stirred for 1 h, trimethylsilylacetylene (1 mL) was then injected, and the suspension was stirred for 30 min at room temperature. Then the mixture was heated to 75°C overnight. The solution was then allowed to cool to room temperature and the solvent was evaporated in vacuo. The crude product was purified by column chromatography on silica gel with petroleum ether as eluent to provide the desired product as a white solid (569 mg, 54%). ^{1}H NMR (400 MHz, Chloroform-d) δ (ppm): 7.59 (d, J = 7.8 Hz, 2H), 7.45 (dd, J = 7.8, 1.4 Hz, 2H), 7.41 (s, 2H), 1.96–1.90 (m, 4H), 1.12–0.98 (m, 12H), 0.77 (t, J = 7.2 Hz, 6H), 0.51 (t, J = 7.3 Hz, 4H), 0.29 (s, 18H). IR: (C≡C) 2156 cm^{-1}.

4.4 | Synthesis of C4

Add a mixture of methanol and dichloromethane containing C2 (264 mg, 0.5 mmol) and K_2CO_3 (276 mg, 2 mmol) to a 100 mL flask, and stir the solution for 24 h under the protection of N_2. Then dichloromethane was added, and the organic phase was washed with a saturated solution of NaCl and dried from anhydrous $MgSO_4$. The crude product was collected by a vacuum rotary evaporator and purified by silica gel column chromatography to obtain the desired product as a yellow oily product (134 mg, 70%). ^{1}H NMR (400 MHz, Chloroform-d) δ (ppm): 7.63 (d, J = 7.8 Hz, 2H), 7.48 (dd, J = 7.8, 1.5 Hz, 2H), 7.46 (s, 2H), 3.16 (s, 2H), 1.96–1.91 (m, 4H), 1.13–1.00 (m, 12H), 0.76 (t, J = 7.2 Hz, 6H), 0.56 (ddt, J = 12.0, 7.5, 4.3 Hz, 4H). IR: (C≡C) 2106 cm^{-1}, (C≡C–H) 3298 cm^{-1}.

4.5 | Synthesis of C5

Under the protection of N_2, CuI (57 mg, 0.3 mmol), $Pd(PPh_3)_4$ (173 mg, 0.15 mmol), and 2,4,6-tris(4-bromophenyl)-1,3,5-triazine (T1, 546 mg, 1 mmol) were added to the freshly distilled triethylamine (30 mL) and tetrahydrofuran (20 mL) solution. After the solution was stirred for 30 min, trimethylsilylacetylene (1 mL) was injected. The mixture was heated to reflux and kept for 24 h. Then the solution was allowed to cool to room temperature, and the solvent was evaporated in vacuo. The crude product was purified by column chromatography on silica gel with petroleum ether and ethyl acetate as eluent (20/1, v/v), yielding the white solid (297 mg, 49.7%). ^{1}H NMR (400 MHz, Chloroform-d) δ (ppm): 8.62 (d, J = 8.2 Hz, 6H), 7.58 (d, J = 8.2 Hz, 6H), 0.23 (s, 27H).

4.6 | Synthesis of C6

A 100 mL flask was added C5 (598 mg, 1 mmol) and K_2CO_3 (690 mg, 5 mmol) in methanol (30 mL), and the solution was stirred overnight under the protection of N_2. After evaporation of methanol, the residue was dissolved in dichloromethane and extracted with deionized water three times. The crude product was collected by a vacuum rotary evaporator and then recrystallized from boiling dichloromethane, yielding a yellowish solid (211 mg, 55.3%). ^{1}H NMR (400 MHz, Chloroform-d) δ (ppm): 8.67–8.63 (m, 6H), 7.65–7.61 (m, 6H), 3.22 (s, 3H).

4.7 | Synthesis of CPP1

The reactant C6 (95 mg, 0.25 mmol) and CuCl (25 mg, 0.25 mmol) were added to a two-necked flask (50 mL), and pyridine (20 mL) was injected under an N_2 atmosphere. Stir at room temperature for 36 h. The solvent was removed by filtration, and the residue was further washed with deionized water and acetone in turn. At last, the desired dark brown CPP1 was obtained (58 mg) after drying.

4.8 | Synthesis of CPP2

A two-necked flask (50 mL) with a stir bar was added C2 (88 mg, 0.15 mmol), T1 (55 mg, 0.1 mmol), $Pd(PPh_3)_4$ (8 mg, 0.007 mmol), and K_2CO_3 (69 mg, 0.5 mmol). Then deionized water (5 mL) and redistilled tetrahydrofuran (20 mL) were injected into the flask under N_2 atmosphere. The mixture was heated to reflux overnight. After cooling to room temperature, the solvent was removed by filtration, and the residue was further washed with deionized water, ethanol, and tetrahydrofuran, respectively. At last, the faint yellow CPP2 was obtained (97 mg) after drying.

4.9 | Synthesis of CPP3

Under the protection of N_2, a mixture of C4 (38 mg, 0.1 mmol) and T1 (36 mg, 0.066 mmol) in freshly distilled triethylamine (9 mL)

27662098, 2026, 1, Downloaded from https://onlinelibrary.wiley.com/doi/10.1002/EXP.20250234 by CochraneChina, Wiley Online Library on [08/06/2026]. See the Terms and Conditions (https://onlinelibrary.wiley.com/terms-and-conditions) on Wiley Online Library for rules of use; OA articles are governed by the applicable Creative Commons License

and redistilled tetrahydrofuran (15 mL) was added $Pd(PPh_3)_4$ (6 mg, 0.005 mmol) and CuI (1.9 mg, 0.01 mmol). Then the mixture was heated to reflux overnight. After cooling to room temperature, the solvent was removed by filtration, and residue was further washed with deionized water and tetrahydrofuran in turn. At last, the yellow CPP3 was obtained (46 mg) after drying.

4.10 | Preparation of CPPs Solution

The CPP1 powder (50 mg) was added to chlorobenzene (30 mL) and smashed by sonication treatment with a 12 mm probe (500 W) for 6 h to obtain a suspension, during which the suspension was cooled in an ice bath. Following sonication, CPP1 dispersion was stirred in a 50°C water bath environment for 24 h. The CPP1 dispersion in chlorobenzene was filtered using filters of 0.22 μm. After drying the solution (200 μL) in a 60°C air blast drying oven for 5 h to remove chlorobenzene, chloroform (1 mL) was added immediately, resulting in a clear and homogeneous dispersion of CPP1 in chloroform. The preparation methods of CPP2 and CPP3 solutions are similar to CPP1 (Figure S11).

4.11 | Preparation of BCDs@CPP2 Composite

The composite was prepared by mixing BCDs with CPP2. The synthesis of BCDs can be found in our previous work [26]. BCDs (5 mg) were added to a CPP2 chloroform solution (1 mL). This mixture was then sonicated for 1 h to ensure adequate attachment of BCDs onto CPP2. Subsequently, the resulting mixture was filtered through a 0.45 μm filter to obtain BCDs@CPP2 composite solution that was used for fabricating the memristors.

4.12 | Preparation of Heat-Triggered DA Release System (DA@ZIF-8@PVA Hydrogel)

(1) For the synthesis of ZIF-8, 1190 mg of $Zn(NO_3)_2{\cdot}6H_2O$ and 1314 mg of 2-methylimidazole were each dissolved in 45 mL methanol. The mixed solution was vigorously stirred for 1 h at room temperature. Then, the mixture was poured into a poly(tetrafluoroethylene) (Teflon)-lined stainless autoclave, which was transferred to an oven at 120°C immediately and kept for 4 h. After the autoclave was cooled down, the reaction solution was centrifuged. The as-obtained ZIF-8 was centrifuged, which was washed with *N*,*N*-dimethylformamide three times and methanol twice. Finally, the purified precipitate was further dried in the oven, and the white ZIF-8 was obtained. (2) For the synthesis of PVA hydrogel, initially, 3.77 g of low-MW PVA (13,000–23,000) and 0.23 g of high-MW PVA (146,000–186,000) were dissolved in 90°C deionized water with vigorous stirring to ensure complete dissolution, forming a PVA aqueous solution. Methyl blue was added to make the PVA hydrogel flow easier to observe. This solution was then subjected to a series of freeze–thaw cycles: one cycle of –20°2C for 24 h and room temperature for 4 h, followed by four cycles of −20°C for 4 h and room temperature for 4 h, ultimately leading to the formation of a PVA hydrogel. (3) To prepare DA release system (DA@ZIF-8@PVA hydrogel), ZIF-8 (1 mg) was dispersed in deionized water (10 mL) under ultrasonication for 20 min. The dispersed ZIF-8 solution was deoxygenated by bubbling N_2 for 30 min, followed by the addition of DA powder (100 mg). The mixed solution was stirred overnight in a vacuum glove box to avoid DA polymerization. Then, the solution was centrifuged and washed with deionized water. The obtained ZIF-8 loaded with DA (DA@ZIF-8) was used as another hydrogel precursor to prepare DA release system via the above freeze–thaw cycles.

4.13 | Fabrication of Memristors

Before commencing the fabrication of memristors, it is imperative to clean the indium tin oxide (ITO) glass substrates. The substrates were cleaned on consecutive sonication with acetone, deionized water, and isopropanol for 30 min, respectively, followed by drying to eliminate moisture content. Furthermore, the cleaned substrate underwent an ultraviolet-ozone treatment (30 min) to enhance interfacial affinity. Additionally, CPPs (60 μL) or its composite solution were taken to fabricate the film using the same revolution speed (1500 rpm) and time (40 s) as the BCDs-based memristor. Then, the functional layer film was annealed for 30 min at 80°C. Finally, a layer of Al top electrode was evaporated on the functional layer using the thermal evaporation method combined with different mask templates. All the electrical measurements were used by the semiconductor parameter analyzer Keithley 4200 and FS-Pro.

4.14 | Fabrication of ANIC

An array of memristors was fabricated on a flexible PET substrate, which was connected in series with a heater. The memristors controlled the releasing behavior of PVA hydrogel through the heater. A PDMS microfluidic film loaded with the DA release system was attached closely onto the heater. The PDMS microfluidic film was prepared by crosslinking and solidifying precursors in a pre-designed mold. The melted PVA with DA flowed through the PDMS channels to a terminal circular region and ultimately towards the postsynaptic neuron. The integration of the composite-based memristor array, PDMS microfluidic film, and DA release system forms ANIC (Figure S19).

4.15 | Cell Culture

PC12 cells were routinely cultured in High glucose Dulbecco's modified Eagle's medium with 10 % fetal bovine serum, and 1% penicillin/streptomycin at 37°C under 5% CO_2 in a humidified incubator.

4.16 | Fluorescence Ca^{2+} Imaging

Ca^{2+} signal can be used to judge whether PC 12 cells are activated by released DA from the ANIC. PC12 cells were treated by Fluo-4 AM probe for 30 min. Then, the probe solution was removed and dishes were washed with PBS. The solution containing DA released by the ANIC was incubated with PC12 cells. Subsequently, cells were observed at different time by Ca^{2+} imaging using confocal laser scanning microscope (OLMPUS BX60 confocal laser scanning microscope).

27662098, 2026, 1, Downloaded from https://onlinelibrary.wiley.com/doi/10.1002/EXP.20250234 by CochraneChina, Wiley Online Library on [08/06/2026]. See the Terms and Conditions (https://onlinelibrary.wiley.com/terms-and-conditions) on Wiley Online Library for rules of use; OA articles are governed by the applicable Creative Commons License

Acknowledgments

This work was funded by the financial support from the National Natural Science Foundation of China (31870934, 12272251, 62205235, 62204157), Postdoctoral Fellowship Program of CPSF (GZC20251905), Foundational Research Project of Shanxi Province (202503021212068, 20210302123164), Basic Research Plan of Shanxi Province (202403021211010), Shanxi Scholarship Council of China (2024-058), Science and Education Cultivation Fund of the National Cancer and Regional Medical Center of Shanxi Provincial Cancer Hospital (TD2023003), and Shanxi Center of Technology Innovation for Controlled and Sustained Release of Nano-drugs (202104010911026). The authors extend their gratitude to Baobao Zhao from Scientific Compass (www.shiyanjia.com) for providing invaluable assistance with the conductive atomic force microscopy analysis.

Conflicts of Interest

The authors declare no conflicts of interest.

Data Availability Statement

Data supporting the results of this study are available from the corresponding author upon reasonable request.

References

1. S. Biswas, H.-W. Jang, Y. Lee, et al., "Recent Advancements in Implantable Neural Links Based on Organic Synaptic Transistors," *Exploration* 4 (2024): 20220150, https://doi.org/10.1002/EXP.20220150.

2. J. Kwon, J. Kim, J. Kim, S. Chun, K. Soh, and J. Yoon, "Artificial Sensory System Based on Memristive Devices," *Exploration* 4 (2024): 20220162, https://doi.org/10.1002/EXP.20220162.

3. J. Yan, J. Armstrong, F. Scarpa, and A. Perriman, "Hydrogel-Based Artificial Synapses for Sustainable Neuromorphic Electronics," *Advanced Materials* 36 (2024): 2403937, https://doi.org/10.1002/adma.202403937.

4. T. Wang, M. Wang, J. Wang, et al., "A Chemically Mediated Artificial Neuron," *Nature Electronics* 5 (2022): 586–595, https://doi.org/10.1038/s41928-022-00803-0.

5. J. Chen, C. Zhu, G. Cao, et al., "Mimicking Neuroplasticity via Ion Migration in van der Waals Layered Copper Indium Thiophosphate," *Advanced Materials* 34 (2022): 2104676, https://doi.org/10.1002/adma.202104676.

6. L. Dong, S. Yuan, G. Wei, et al., "Artificial Optoelectronic Synapse Based on Violet Phosphorus Microfiber Arrays," *Small* 20 (2023): 2306998, https://doi.org/10.1002/smll.202306998.

7. X. Liu, C. Sun, X. Ye, et al., "Neuromorphic Nanoionics for Human-Machine Interaction: From Materials to Applications," *Advanced Materials* 36 (2024): 2311472, https://doi.org/10.1002/adma.202311472.

8. B. Sun, Y. Chen, G. Zhou, et al., "Memristor-Based Artificial Chips," *ACS Nano* 18 (2023): 14–27, https://doi.org/10.1021/acsnano.3c07384.

9. Z. Liu, J. Tang, B. Gao, et al., "Neural Signal Analysis With Memristor Arrays Towards High-efficiency Brain-Machine Interfaces," *Nature Communications* 11 (2020): 4234, https://doi.org/10.1038/s41467-020-18105-4.

10. S. Hus, R. Ge, P. Chen, et al., "Observation of Single-Defect Memristor in an MoS_2 Atomic Sheet," *Nature Nanotechnology* 16 (2021): 58–62, https://doi.org/10.1038/s41565-020-00789-w.

11. K. Woo, H. Park, N. Ghenzi, et al., "Memristors With Tunable Volatility for Reconfigurable Neuromorphic Computing," *ACS Nano* 18 (2024): 17007–17017, https://doi.org/10.1021/acsnano.4c03238.

12. W. Yang, H. Kan, G. Shen, and Y. Li, "A Network Intrusion Detection System With Broadband WO_{3-x}/WO_{3-x}-Ag/WO_{3-x} Optoelectronic Memristor," *Advanced Functional Materials* 34 (2024): 2312885, https://doi.org/10.1002/adfm.202312885.

13. K. Liu, B. Dang, T. Zhang, et al., "Multilayer Reservoir Computing Based on Ferroelectric α-In_2Se_3 for Hierarchical Information Processing," *Advanced Materials* 34 (2022): 2108826, https://doi.org/10.1002/adma.202108826.

14. G. Zhou, J. Li, Q. Song, et al., "Full Hardware Implementation of Neuromorphic Visual System Based on Multimodal Optoelectronic Resistive Memory Arrays for Versatile Image Processing," *Nature Communications* 14 (2023): 8489, https://doi.org/10.1038/s41467-023-43944-2.

15. S. Keene, C. Lubrano, S. Kazemzadeh, et al., "A Biohybrid Synapse With Neurotransmitter-Mediated Plasticity," *Nature Materials* 19 (2020): 969–973, https://doi.org/10.1038/s41563-020-0703-y.

16. Y. Lee, H.-L. Park, Y. Kim, and T.-W. Lee, "Organic Electronic Synapses With Low Energy Consumption," *Joule* 5 (2021): 794–810, https://doi.org/10.1016/j.joule.2021.01.005.

17. Y. Huang, Y. Gu, S. Mohan, et al., "Reliability Improvement and Effective Switching Layer Model of Thin-Film MoS_2 Memristors," *Advanced Functional Materials* 33 (2023): 2214250.

18. H. Hu, A. Scholz, C. Dolle, et al., "Inkjet-Printed Tungsten Oxide Memristor Displaying Non-Volatile Memory and Neuromorphic Properties," *Advanced Functional Materials* 34 (2023): 2302290, https://doi.org/10.1002/adfm.202302290.

19. D. Garbin, E. Vianello, O. Bichler, et al., "HfO_2-based OxRAM Devices as Synapses for Convolutional Neural Networks," *IEEE Transactions on Electron Devices* 62 (2015): 2494–2501, https://doi.org/10.1109/TED.2015.2440102.

20. Y. Lin, Z. Wang, X. Zhang, et al., "Photoreduced Nanocomposites of Graphene Oxide/N-Doped Carbon Dots Toward All-Carbon Memristive Synapses," *NPG Asia Materials* 12 (2020): 64, https://doi.org/10.1038/s41427-020-00245-0.

21. A. Cooper, "Conjugated Microporous Polymers," *Advanced Materials* 21 (2009): 1291–1295, https://doi.org/10.1002/adma.200801971.

22. R. Dawson, A. Cooper, and D. Adams, "Nanoporous Organic Polymer Networks," *Progress in Polymer Science* 37 (2012): 530–563, https://doi.org/10.1016/j.progpolymsci.2011.09.002.

23. D. Taylor, S. Dalgarno, Z. Xu, and F. Vilela, "Conjugated Porous Polymers: Incredibly Versatile Materials With Far-Reaching Applications," *Chemical Society Reviews* 49 (2020): 3981–4042, https://doi.org/10.1039/C9CS00315K.

24. T. Li, H. Yu, Z. Xiong, Z. Gao, Y. Zhou, and S.-T. Han, "2D Oriented Covalent Organic Frameworks for Alcohol-Sensory Synapses," *Materials Horizons* 8 (2021): 2041–2049, https://doi.org/10.1039/D1MH00315A.

25. S. Wang, S. Huang, M. Yao, Y. Zhang, and Z. Niu, "Engineering Active Sites of Polyaniline for $AlCl_2^+$ Storage in an Aluminum-Ion Battery," *Angewandte Chemie, International Edition* 59 (2020): 11800–11807, https://doi.org/10.1002/anie.202002132.

26. H. Hao, M. Wang, Y. Cao, et al., "Boron-Doped Engineering for Carbon Quantum Dots-Based Memristors With Controllable Memristance Stability," *Small Methods* 8 (2024): 2301454, https://doi.org/10.1002/smtd.202301454.

27. H. Chen, W. Liu, A. Laemont, et al., "A Visible-Light-Harvesting Covalent Organic Framework Bearing Single Nickel Sites as a Highly Efficient Sulfur-Carbon Cross-Coupling Dual Catalyst," *Angewandte Chemie International Edition* 133 (2021): 10915–10922, https://doi.org/10.1002/ange.202101036.

28. A. Elewa, A. F. M. El-Mahdy, M. Elsayed, M. G. Mohamed, S.-W. Kuo, and H.-H. Chou, "Sulfur-Doped Triazine-Conjugated Microporous Polymers for Achieving the Robust Visible-Light-Driven Hydrogen Evolution," *Chemical Engineering Journal* 421 (2021): 129825, https://doi.org/10.1016/j.cej.2021.129825.

29. C. Ru, T. Zhou, J. Zhang, et al., "Introducing Secondary Acceptors Into Conjugated Polymers to Improve Photocatalytic Hydrogen Evolution," *Macromolecules* 54 (2021): 8839–8848, https://doi.org/10.1021/acs.macromol.1c00705.

27662098, 2026, 1, Downloaded from https://onlinelibrary.wiley.com/doi/10.1002/EXP.20250234 by CochraneChina, Wiley Online Library on [08/06/2026]. See the Terms and Conditions (https://onlinelibrary.wiley.com/terms-and-conditions) on Wiley Online Library for rules of use; OA articles are governed by the applicable Creative Commons License

30. Y. Zhao, Y. Yuan, Y. Xu, et al., "Fine-Regulating Ultramicropores in Porous Carbon via a Self-Sacrificial Template Route for High-Performance Supercapacitors," *Nanoscale* 13 (2021): 1961–1969, https://doi.org/10.1039/D0NR07480B.

31. R. Kulkarni, J. Huang, M. Trunk, et al., "Direct Growth of Crystalline Triazine-Based Graphdiyne Using Surface-Assisted Deprotection-Polymerisation," *Chemical Science* 12 (2021): 12661–12666, https://doi.org/10.1039/D1SC03390E.

32. Q. Khan, N. Jia, G. Tian, S. Qi, and D. Wu, "Triggering WORM/SRAM Memory Conversion in a Porphyrinated Polyimide via Zn Complexation as the Internal Electrode," *The Journal of Physical Chemistry C* 121 (2017): 9153–9161, https://doi.org/10.1021/acs.jpcc.7b01732.

33. Y. Zhong, Y. Zhang, J. Wang, et al., "Advancing Extreme-Temperature-Tolerant Zinc-Air Batteries Through Photothermal Transition Metal Sulfide Heterostructures," *Energy & Environmental Science* 18 (2025): 991–1001, https://doi.org/10.1039/D4EE03240C.

34. W. Wang, J. Wang, S. Pan, et al., "Crafting of Photothermal Cobalt/Sulfur Doped Manganese Selenide for Extreme-Temperature-Tolerant Flexible Zinc-Air Batteries," *Advanced Functional Materials* (2025): 2425430, https://doi.org/10.1002/adfm.202425430.

35. H.-W. Zhou, C. Zhao, Z.-Y. Zhao, et al., "Flexible and Multifunctional Triboelectric Nanogenerator Based on Liquid Metal/Polyvinyl Alcohol Hydrogel for Energy Harvesting and Self-Powered Wearable Human-Machine Interaction," *Rare Metals* 43 (2024): 1186–1196, https://doi.org/10.1007/s12598-023-02518-3.

36. Y. Chen, Z. Wang, Y. He, et al., "Light-Enabled Reversible Self-Assembly and Tunable Optical Properties of Stable Hairy Nanoparticles," *Proceedings of the National Academy of Sciences of the United States of America* 115 (2018): E1391–E1400.

37. X. Zhang, S. Pan, H. Song, et al., "Photothermal Effect Enables Markedly Enhanced Oxygen Reduction and Evolution Activities for High-Performance Zn-Air Batteries," *Journal of Materials Chemistry A* 9 (2021): 19734–19740, https://doi.org/10.1039/D1TA03652A.

38. H. Guo, L. Shi, Z. Shi, Y. He, and Y. Zhu, "Direct Synthesis of High Quantum Yield Lead-Free $CsCu_2I_3$ Powder in Water and Its Application in Yellow LED," *Exploration* 5 (2025): 20240004, https://doi.org/10.1002/EXP.20240004.

39. H. Chen, Y. Kang, D. Pu, et al., "Introduction of Defects in Hexagonal Boron Nitride for Vacancy-Based 2D Memristors," *Nanoscale* 15 (2023): 4309–4316, https://doi.org/10.1039/D2NR07234C.

40. H. Zhao, Z. Dong, H. Tian, et al., "Atomically Thin Femtojoule Memristive Device," *Advanced Materials* 29 (2017): 1703232, https://doi.org/10.1002/adma.201703232.

41. S.-O. Park, H. Jeong, J. Park, J. Bae, and S. Choi, "Experimental Demonstration of Highly Reliable Dynamic Memristor for Artificial Neuron and Neuromorphic Computing," *Nature Communications* 13 (2022): 2888, https://doi.org/10.1038/s41467-022-30539-6.

42. J. Liang, W. Li, J. Chen, et al., "Carbon Dots as an Electron Extractant for Enhanced Photocatalytic Antibacterial Activity of Covalent Organic Frameworks," *Journal of Materials Chemistry A* 10 (2022): 23384–23394, https://doi.org/10.1039/D2TA03978H.

43. H. Hao, L. Yan, M. Wang, Y. Cao, J. He, and Y. Yang, "Research Process of Carbon Dots in Memristors," *Advanced Electronic Materials* 9 (2023): 2201195, https://doi.org/10.1002/aelm.202201195.

44. J.-Q. Yang, R. Wang, Y. Ren, et al., "Neuromorphic Engineering: From Biological to Spike-Based Hardware Nervous Systems," *Advanced Materials* 32 (2020): 2003610, https://doi.org/10.1002/adma.202003610.

45. T. Zeng, Z. Yang, J. Liang, et al., "Flexible and Transparent Memristive Synapse Based on Polyvinylpyrrolidone/N-Doped Carbon Quantum Dot Nanocomposites for Neuromorphic Computing," *Nanoscale Advances* 3 (2021): 2623–2631, https://doi.org/10.1039/D1NA00152C.

46. R. Zucker and W. Regehr, "Short-Term Synaptic Plasticity," *Annual Review of Physiology* 64 (2002): 355–405, https://doi.org/10.1146/annurev.physiol.64.092501.114547.

47. G. Voglis and N. Tavernarakis, "The Role of Synaptic Ion Channels in Synaptic Plasticity," *EMBO Reports* 7 (2006): 1104–1110, https://doi.org/10.1038/sj.embor.7400830.

48. Q. Liu, L. Yin, C. Zhao, et al., "All-in-One Metal-Oxide Heterojunction Artificial Synapses for Visual Sensory and Neuromorphic Computing Systems," *Nano Energy* 97 (2022): 107171, https://doi.org/10.1016/j.nanoen.2022.107171.

49. F. Yu, L. Zhu, H. Xiao, W. Gao, and Y. Guo, "Restickable Oxide Neuromorphic Transistors With Spike-Timing-Dependent Plasticity and Pavlovian Associative Learning Activities," *Advanced Functional Materials* 28 (2018): 1804025, https://doi.org/10.1002/adfm.201804025.

50. I. Mansuy, M. Mayford, B. Jacob, E. Kandel, and M. Bach, "Restricted and Regulated Overexpression Reveals Calcineurin as a Key Component in the Transition From Short-Term to Long-Term Memory," *Cell* 92 (1998): 39–49, https://doi.org/10.1016/S0092-8674(00)80897-1.

51. Z. Lian and L. Ye, "Effect of PEO on the Network Structure of PVA Hydrogels Prepared by Freezing/Thawing Method," *Journal of Applied Polymer Science* 128 (2013): 3325–3329, https://doi.org/10.1002/app.38544.

52. C. Liu, P. Goel, and P. Kaeser, "Spatial and Temporal Scales of Dopamine Transmission," *Nature Reviews Neuroscience* 22 (2021): 345–358, https://doi.org/10.1038/s41583-021-00455-7.

53. J. Li, C.-L. Sun, P. R. An, et al., "Construction of Dopamine-Releasing Gold Surfaces Mimicking Presynaptic Membrane by On-Chip Electrochemistry," *Journal of the American Chemical Society* 141 (2019): 8816–8824, https://doi.org/10.1021/jacs.9b01003.

Supporting Information

Additional supporting information can be found online in the Supporting Information section.

Supporting File 1: exp270132-sup-0001-SuppMat.docx.

27662098, 2026, 1, Downloaded from https://onlinelibrary.wiley.com/doi/10.1002/EXP.20250234 by CochraneChina, Wiley Online Library on [08/06/2026]. See the Terms and Conditions (https://onlinelibrary.wiley.com/terms-and-conditions) on Wiley Online Library for rules of use; OA articles are governed by the applicable Creative Commons License