Check for updates

RESEARCH ARTICLE OPEN ACCESS

Sunlight-Driven Fixation of CO_2 to Cyclic Carbonates Using Carbon Dots as a Photothermal Catalyst

Ruijia Wang[1] | Hongda Guo[1] | Tao Zhang[1] | Xiaoxia Chen[1] | Min Ge[1] | Shujun Li[1,2] | Jian Li[2] | Bing Tian[1,2] | Bernd Strehmel[3] | Shouxin Liu[1,2] | Andrey L. Rogach[4,5] | Tony D. James[6,7] | Zhijun Chen[1,2,8]

[1]State Key Laboratory of Woody Oil Resources Utilization, Northeast Forestry University, Harbin, China | [2]Key Laboratory of Bio-based Material Science and Technology of Ministry of Education, Northeast Forestry University, Harbin, China | [3]Department of Chemistry, Institute for Coatings and Surface Chemistry, Niederrhein University of Applied Sciences, Krefeld, Germany | [4]Department of Materials Science and Engineering, Centre for Functional Photonics (CFP), City University of Hong Kong, Hong Kong SAR, China | [5]IT4Innovations, VSB-Technical University of Ostrava, Ostrava-Poruba, Czech Republic | [6]Department of Chemistry, University of Bath, Bath, UK | [7]School of Chemistry and Chemical Engineering, Henan Normal University, Xinxiang, China | [8]Heilongjiang International Joint Laboratory of Advanced Bio-Mass Materials, Northeast Forestry University, Harbin, China

Correspondence: Bing Tian (tianbing@nefu.edu.cn) | Shouxin Liu (liushouxin@126.com) | Andrey L. Rogach (andrey.rogach@cityu.edu.hk) | Tony D. James (T.D.James@bath.ac.uk) | Zhijun Chen (chenzhijun@nefu.edu.cn)

Received: 5 February 2025 | **Revised:** 17 April 2025 | **Accepted:** 11 October 2025

Keywords: carbon dioxide | carbon dots | cyclic carbonate | photothermal catalysis | sunlight utilization

ABSTRACT

Fixation of CO_2 through photocatalytic cycloaddition with epoxides to synthesize cyclic carbonates is an important but challenging process. In this work, carbon dots (CDs) synthesized from gallic acid and polyethylenimine are used for the efficient catalytic cycloaddition of CO_2 with epoxides in the absence of any solvent, additives, and halides, and importantly upon irradiation by natural sunlight. Specifically, carbon dots generated thermal energy and electrons upon solar irradiation, which together with their surface N-sites activated the inert CO_2. Meanwhile, epoxides were activated by the surface hydroxyl and carboxylic groups of the carbon dots, which reacted with activated CO_2 at solar thermal-induced high temperatures. The CDs shows excellent stability and recyclability during the catalysis. A 1000 mmol scale reaction for cyclic carbonate synthesis performed well upon irradiation with natural sunlight in the presence of CDs, showing great potential for the industrial application due to the simple, mild, and energy-saving process.

1 | Introduction

Cyclic carbonates are organic compounds with many useful properties, which exhibit widespread applications as aprotic high-boiling polar solvents, electrolytes for batteries, precursors for polymeric materials, fuel additives, plastic materials, and synthetic intermediates [1–3]. In industry, one main route for producing cyclic carbonates is the cycloaddition reaction of CO_2 with epoxides. Importantly, the conversion of CO_2 to high value-added chemicals is of vital importance in terms of CO_2 fixation from the atmosphere [4–7]. To avoid the harsh reaction conditions required, such as high temperature, high pressure etc., and to enhance the conversion yield of the reaction between CO_2 and epoxides, several efficient catalysts have been suggested, which include both homogeneous catalysts (Schiff bases, ionic liquids, metal complexes) [8–12] and heterogeneous catalysts (covalent-organic frameworks, metal-organic frame-works, mesoporous oxides, porous polymers) (Figure 1A) [13–23]. Amongst these catalysts, heterogeneous photocatalysts received particularly attention, since they can catalyze the reaction in an energy-efficient and environmentally friendly manner [24–35]. However, most of these photocatalysts suffer from several challenges,

This is an open access article under the terms of the Creative Commons Attribution License, which permits use, distribution and reproduction in any medium, provided the original work is properly cited.

© 2026 The Author(s). *Exploration* published by Henan University and John Wiley & Sons Australia, Ltd.




FIGURE 1 | Background and catalytic synthesis of cyclic carbonates. (A) Catalytic synthesis of cyclic carbonates using epoxides and CO_2. (B) Structure of CDs. (C) CDs-catalyzed reaction of CO_2 and epoxides for cyclic carbonates synthetic procedure used in this research under sunlight via a photothermal process.

hindering their practical applications. They exhibit low intrinsic catalytic reactivity, leading to necessity of co-catalysts such as active Lewis-acidic metal complexes or environmentally harmful halide ions (see comparison in Supporting Information); require a complicated/expensive synthesis and/or external thermal heating/high pressure; and can only work well under laboratory conditions, and could not be efficiently activated using natural sunlight.

Recently, CDs have appeared as novel environmentally friendly and easy to produce carbon nanomaterials [36–38], which enable electron photo-transfer and photothermal conversion, rendering them as promising photocatalysts (Figure 1B) [39–41]. In particular, CDs which are small colloidal nanoparticles with a large variety of surface moieties have been shown to exhibit high photothermal catalytic efficiency when they were coupled with conjugated organic structures or metal-incorporating materials [42–46]. However, using CDs as photothermal catalysts without such a modification has rarely been reported [47].


Herein, we employ CDs synthesized from gallic acid (GA) and polyethylenimine (PEI) via a simple hydrothermal process, as photothermal catalysts for the reaction between CO_2 and epoxides under sunlight irradiation (Figure 1C). These CDs exhibited highly efficient solar-to-thermal conversion with an efficiency of 54%, providing thermal energy for activating the reaction, and at the same time the photo-induced electron activation of CO_2. Meanwhile, the N-sites and the surface polar groups (hydroxyl and carboxylic acid) of the CDs were able to efficiently activate CO_2 and epoxides, respectively. Our study offers an efficient and sustainable approach using CDs for CO_2 conversion in a metal-free, additive-free, and solvent-free manner under irradiation by sunlight.

2 | Results and Discussions

2.1 | Reaction Design

GA and PEI which contain abundant polar groups (hydroxyl, carboxylic, and amino) were selected as CDs precursors. The CDs were synthesized by a hydrothermal process (180°C, 8 h) using a 1:1 molar ratio of GA/PEI (Figure 2A). As shown by the transmission electron microscopic (TEM) images, the as-prepared CDs have an average size of 2.3 ± 0.2 nm (Figure 2B), and are spherical in shape. The high-resolution TEM image (inset in Figure 2B) revealed a lattice spacing of 0.21 nm, attributed to the (100) lattice fringes of graphene. Their X-ray diffraction (XRD) pattern exhibits a broad peak around 20° (Figure S1), a typical signal of carbon dots [48]. The Raman spectrum of the CDs exhibits two peaks at 1376.9 and 1559.3 cm^{-1} that correspond to the disordered (D band) and graphite (G band) of carbon materials (Figure 2C). An I_G/I_D ratio of 1.1 indicated a high extent of graphitization in the CDs, which should be beneficial for photothermal conversion [49, 50]. The Fourier transform infrared (FT-IR) spectrum of the CDs displayed an enhanced absorption band at 3110–3631 cm^{-1}, belonging to the stretching vibrations from N—H and O—H groups (Figure S2). The peaks at 1658 cm^{-1} and 1578 cm^{-1} belong to C═O/C═N stretching vibrations and N—H bending vibrations, respectively, and the peaks at 1450 cm^{-1}, 1348 cm^{-1}, and 1125 cm^{-1} can be assigned to aromatic C—N, C—O, and alkyl C—N stretching, respectively. The typical broad peaks in ^1H nuclear magnetic resonance spectroscopy (NMR) spectra shows the successful synthesis of CDs (Figure 3). The hydroxyl, carboxylic acid, and amino groups present at the surface of CDs are beneficial for activating the epoxides via hydrogen bonding interaction [8]. X-ray photoelectron spectra (XPS) of CDs (Figure S4) are consistent with the FT-IR analysis. Specifically, the high-resolution N 1s XPS

27662098, 2026, 1, Downloaded from https://onlinelibrary.wiley.com/doi/10.1002/EXP.20250043 by CochraneChina, Wiley Online Library on [08/06/2026]. See the Terms and Conditions (https://onlinelibrary.wiley.com/terms-and-conditions) on Wiley Online Library for rules of use; OA articles are governed by the applicable Creative Commons License



Entry	1	2	3	4	5	6	7
Catalyst	CDs (2.5 wt%)	CDs (5 wt%)	PEI-CDs (5 wt%)	GA-CDs (5 wt%)	PEI (5 wt%)	GA (5 wt%)	PEI/GA (5 wt%)
System temp. (°C)	90	100	62	57	58	52	58
Yield (%)	75	90	7	0	0	0	0

FIGURE 2 | Basic characteristics of CDs and photocatalytic transformation of CO_2 with epoxides to cyclic carbonates. (A) Hydrothermal reaction leading to the formation of CDs. (B) TEM image of CDs; insets show lattice spacing and size distribution of CDs. (C) Raman spectrum of CDs. (D) UV–vis–NIR absorption spectrum (in blue) of CDs; the solar spectrum is also provided in orange. (E) Temperature change of CDs under ten on/off cycles of simulated sunlight irradiation (0.7 W cm^{-2}). (F) Temperature changes of CDs in epoxide **1** under simulated sunlight irradiation ranging from 0.1 to 0.9 W cm^{-2}. (G) Optimization of the reaction of CO_2 with epoxide **1**. The reaction yield was determined by ^1H NMR using CF_3-DMA as an internal standard. (H) Time course of CDs-catalyzed reaction of epoxide 1 with CO_2 using photothermal (simulated sunlight) and thermal conditions (oil bath).

spectrum revealed strong signals from the pyridinic (399.1 eV), pyrrolic (400.1 eV), and graphitic (402.1 eV) nitrogen, respectively. These N-containing moieties will be useful as efficient CO_2 activation and chemiadsorption sites which was also identified by CO_2 adsorption-desorption isotherms of CDs (Figure S5) [51–53].

The UV–visible (UV–vis)–near-IR (NIR) absorption spectrum (Figure 2D; Figures S6 and S7) indicates that the CDs have a broad absorption extending all the way from the UV–vis to the IR region (250–2500 nm), with a significant absorption over the visible light region, which means that they can efficiently absorb and utilize the whole spectrum of sunlight. As expected, the CDs powder exhibited excellent photothermal conversion (Figure S8). Importantly, an excellent photothermal conversion efficiency of these CDs equal to 54% was observed, as given in Figure S9. Stability of photothermal catalysts against photobleaching is an important aspect. Figure 2E shows the temperature curves for the CDs after 10 light on/off cycles, which confirm the excellent photothermal stability of the CDs under simulated sunlight irradiation. We subsequently evaluated the photothermal effect of CDs with epoxide **1** in a solvent-free system for reaction with CO_2. As shown in Figure 2F and Figure S10, a mixture of 5 wt% of CDs (41 mg) with 5 mmol of epoxide **1** (0.8 mL) was irradiated under 0.1, 0.3, 0.5, 0.7, and 0.9 W cm^{-2} simulated sunlight, resulting in a change of temperature from initially 26°C to 43, 61, 71, 94, and 104°C within 20 min, respectively. It is worth noting that the epoxide **1** only showed poor photothermal effect under irradiation (Figure S11). Moreover, the thermogravimetric analysis confirms that CDs displays nice thermal stability, which is vital for facilitating the catalytic reaction (Figure S12).

Given that temperatures in the range of 80–120°C are usually applied for the reaction of CO_2 with epoxides in catalytic systems

27662098, 2026, 1, Downloaded from https://onlinelibrary.wiley.com/doi/10.1002/EXP.20250043 by CochraneChina, Wiley Online Library on [08/06/2026]. See the Terms and Conditions (https://onlinelibrary.wiley.com/terms-and-conditions) on Wiley Online Library for rules of use; OA articles are governed by the applicable Creative Commons License

[8], we employed 0.7 W cm^{-2} of irradiation to evaluate the CO_2 conversion using our CDs. The reaction of CO_2 with benzyl glycidyl ether (Figure 2G) was conducted using 5 wt% of CDs under the irradiation of 0.7 W cm^{-2} simulated sunlight (100°C was achieved), yielding cyclic carbonate **1** with an excellent reaction yield of 90% (Entry 2). The yield decreased from 90% to 75% when 2.5 wt% of CDs was used under the same reaction conditions (Entry 1), which was attributed to a reduced system temperature (90°C) caused by a decrease in amounts of CDs. Notably, no reaction occurred in the absence of CDs, either upon solar irradiation or under heating conditions. While the screening of different ratios of GA/PEI and nitrogen sources in the synthesis of photothermal CDs did not afford better results (Table S1). Catalysts consisting of GA, PEI, GA/PEI, and CDs synthesized using either GA or PEI as a sole precursor all exhibited low photothermal conversion and poor catalytic reactivity (Entries 3–7). Notably, when the reaction was carried out with CDs using heating-induced thermal conditions (100°C, oil bath) instead of photothermal conditions, the reaction between CO_2 and epoxides happened but with a decreased yield (74%, Table S1). Additionally, the time course of the reaction showed a much faster generation of cyclic carbonate **1** under photothermal rather than thermal conditions, indicating a significant photochemical activation effect by CDs.

2.2 | Mechanistic Considerations

The photothermal catalytic mechanism of the CDs-catalyzed CO_2 cycloaddition to epoxides was further investigated. Figure 2H shows that that CDs can catalyze this reaction in a dual mode, including both thermal and photothermal catalysis, which means that both photo-induced activation and chemical activation of CDs are involved in the catalytic process. As the polar groups such as —OH, —CO_2H, and —NH_2 play key roles to chemically activating the epoxide through hydrogen-bonding in the metal-free catalytic systems, the catalytic effect of these polar groups on the surface of CDs was evaluated using a functional group blocking strategy. As shown in Figure 3A, the carboxylic acid, amino, and hydroxyl groups on the surface of CDs were selectively protected by methylation, aldimine condensation and acetylation reactions (Figures S13–S19), respectively, and the photothermal effect of these modified CDs was evaluated (the resulting samples were denoted as Me-CDs, Ar-CDs, and Ac-CDs, respectively). These functional group-blocked CDs were then employed for the photothermal and thermal catalysis of the reaction of CO_2 with epoxide **1** (Figure 3B). Notably, under the standard conditions of photothermal catalysis, the temperature of the reaction system could be kept at 97–100°C by irradiation of the modified CDs, which indicates that the protection of surface groups has a negligible effect on photothermal conversion ability of CDs (Figure 3C). The Ar-CDs with protected amino groups exhibited almost identical catalytic reactivity as the original (non-protected) CDs in both photothermal and thermal catalytic systems, indicating that the amino groups on the surface were not essential for activation of both epoxides and CO_2. Moreover, this observation together with the observed absence of catalytic reactivity of the N atom-free GA-CDs indicates that the activation of CO_2 should be attributed to the presence of pyridinic, pyrrolic, and/or graphitic-nitrogen in the CDs core, rather than their surface amino groups. The reactions using the Me-CDs and Ac-CDs with carboxyl acids and hydroxyl groups blocked led to an obvious decrease of the yield of cycloaddition product **1** under both photothermal conditions (76% and 72% yields) and thermal conditions (69% and 59% yields), respectively. These observations suggest that the catalytic ability of surface polar groups on the CDs decreases in the order of —OH > —CO_2H > —NH_2 (Figure 3D).

Given that photo-induced electron transfer in photothermal catalysis to substrates under irradiation can improve the reactivity of the substrate as compared to the corresponding heating-induced thermal catalytic reactions (Figure 2H), we evaluated the importance of photogenerated electrons in this transformation using CDs. Firstly, the radical and hole quenching experiments were conducted to explore the underlying mechanisms. As shown in Figure 4A, the yield of cyclic carbonate **1** under standard reaction conditions was 46% over 8 h, while no reaction occurred in the absence of CDs. When $AgNO_3$ and $Na_2S_2O_3$ were used as the radical scavengers to capture photogenerated electrons, the reaction yield decreased from 46% to 7% and 37%, respectively, indicating the crucial role of photogenerated electrons. In another experiment, ethylenediaminetetraacetic acid disodium salt (EDTA-2Na) and isopropanol were added to the reaction system containing CDs as hole scavengers. An increase in the reaction yield was observed when EDTA-2Na and isopropanol were used (55% and 71%, respectively), indicating that the photogenerated holes do not contribute to the transformation reaction, but rather increase the recombination of photogenerated electrons, leading to lower degree of conversion. To further explore the possible pathway for activation of photogenerated electrons, electron paramagnetic resonance (EPR) measurements were conducted on CDs, using 2,2,6,6-tetramethylpiperidine 1-oxyl (TEMPO) as the spin-labeling agent which could be reduced by photogenerated electrons, leading to a decrease in intensity of the EPR signal. As shown in Figure 4B,D, the EPR signal intensity decreased by 36% under N_2 and 39% in epoxide **1**/N_2 after 3 min irradiation, indicating that the electrons could hardly be transferred to epoxide **1**. A 28% decrease of the signal intensity was observed in the presence of CO_2, indicating the transfer of electrons from the CDs to CO_2 (Figure 4C). When epoxide **1** was added to the CDs under a CO_2 atmosphere, the EPR signal intensity exhibited similar decrease (29%), further confirming the transfer of electrons to CO_2 rather than to epoxide (Figure 4E). This is because the conduction band (CB) of the CDs is located at −1.9 eV (Figures S20–S22), which is enough to activate the CO_2 to $CO_2^{\bullet-}$. To further study the radical species, in situ FT-IR using standard reaction conditions was used for detection of $CO_2^{\bullet-}$. We found that one obvious component with peaks at 1645–1652 cm^{-1}, which was consistent with the characteristic vibration mode of $CO_2^{\bullet-}$ (Figure S23) [54, 55]. Moreover, the EPR experiments in the absence of CO_2 under light irradiation or dark conditions showed that no signal were detectable (Figures S24). Similarly, under CO_2 atmosphere, the signal was also negligible without light irradiation, while strong characteristic peaks of $CO_2^{\bullet-}$ adduct with 5,5-dimethyl-1-pyrroline *N*-oxide (DMPO) (hyperfine splitting constant $A_N = 15.5$ G, $A_{H\beta} = 19.4$ G, spectroscopic splitting factor $g = 2.0041$) could be found under light irradiation, further confirming that in the presence of CDs and light irradiation, CO_2 molecules can be activated to produce $CO_2^{\bullet-}$ radicals (Figure S25) [56, 57]. Based on these observations, an activation pathway by single electron transfer to CO_2 could be proposed for the

27662098, 2026, 1, Downloaded from https://onlinelibrary.wiley.com/doi/10.1002/EXP.20250043 by CochraneChina, Wiley Online Library on [08/06/2026]. See the Terms and Conditions (https://onlinelibrary.wiley.com/terms-and-conditions) on Wiley Online Library for rules of use; OA articles are governed by the applicable Creative Commons License




FIGURE 3 | Mechanistic study of epoxide activation. (A) Functional group blocking strategy for CDs. Me-CDs, Ar-CDs, and Ac-CDs correspond to carboxylic acid, amino, and hydroxyl groups blocked CDs, respectively. (B) Effect of functional groups on the catalytic reactivity of CDs in the reaction of CO_2 with epoxide **1** using photothermal conditions (simulated sunlight) and thermal conditions (oil bath). (C) Effect of selectively protected CDs on the photothermal conversion. (D) Effect of polar groups on the activation of epoxides.

photo-enhanced transformation, which is illustrated in Figure 4F. To further understand if UV or the visible part of the solar spectrum drives the transfer of the electrons from CDs to CO_2, simulated sunlight with or without the UV light band has been checked for the photothermal catalysis. The absence of UV light band had almost no influence on the conversion efficiency for the transformation reaction, which proceeded with 87% yield (Figure 4G, entry 2). Thermal conditions with additional UV irradiation had no effect on the conversion efficiency (Figure 4G, entry 4), resulting in almost the same yield (Figure 4G, entry 3). These results indicate that the CDs-mediated activation process under visible light irradiation can enhance the conversion of CO_2 into cyclic carbonates. We also noticed that both light irradiation and heating failed to initiate the transformation reaction in the absence of CDs (Figure 4G, entries 5 and 6).

Based on these results, a proposed mechanism for the reaction is depicted in Figure 4H. CDs generated thermal energy and electrons upon solar irradiation, and then together with N-sites activated the inert CO_2. Meanwhile, epoxides were efficiently activated by surface hydroxyl and carboxylic groups of CDs through hydrogen-bonding interactions. Thus, activated CO_2 and epoxides could efficiently react at the high temperature induced by solar irradiation of the photothermal CDs. Moreover, according to the control experiments in Figure 2H, thermal conditions afforded cyclic carbonate **1** in 74% yield while photothermal conditions could achieve 90% yield, indicating that the thermal catalysis for this cycloaddition reaction is still the main pathway and the photo-activation for CO_2 could significantly enhance this process. Considering together the experimental evidences and the relevant reported mechanism for this metal- and halogen-free transformation [51–53], the plausible reaction route is shown in Figure 4H: a nucleophilic attack of activated CO_2 (CO_2^- and $CO_2^{\bullet-}$) to epoxide selectively occurred at the terminal C—O bond, leading to ring-opening intermediate. An intramolecular cyclization further produced cyclic carbonate and simultaneously regenerated CDs.

2.3 | Reaction Development Using Sunlight

Using natural sunlight directly in the catalytic reactions represents a significant challenge, since unstable and non-continuous irradiation by sunlight requires catalysts exhibiting an extremely high catalytic reactivity, especially for reactions with prolonged irradiation. As such, a home-made solar reactor was constructed as shown in Figure 5A and Figure S26, where Fresnel lenses were employed as an optical concentrator to increase solar flux, and optical fibers were used as a light conduit for sunlight. With this device, we investigated the photothermal catalytic performance of the CDs operated under natural sunlight. As shown in Figure 5D, the reaction of epoxide **1** with CO_2 irradiated for 8 h using natural sunlight exhibited almost the same efficiency (48% yield) to that of under simulated sunlight (46% yield) (Figure S27). Remarkably, although the reaction was interrupted during the night, the catalytic reactivity of the system could be reactivated by sunlight irradiation during the following day (Figure 5C). The reaction also provided a high yield (87%) under intermittent irradiation for totally 24 h (8 h during the daytime for 3 days). These results demonstrate the practicability of CDs used as photothermal catalysts for CO_2 conversion using abundant but discontinuous natural sunlight.

Given that this system represents a simple and efficient photocatalyst for the reaction of CO_2 with epoxides, the scope of epoxides (Table S2) was investigated using natural sunlight assisted by the device in Figure 5A at 1 atm of CO_2 (Figure 5F). Epoxides bearing a variety of functional groups could successfully react with CO_2, which resulted in formation of the corresponding cyclic carbonates in excellent yields and selectivity (Figure S28)

27662098, 2026, 1, Downloaded from https://onlinelibrary.wiley.com/doi/10.1002/EXP.20250043 by CochraneChina, Wiley Online Library on [08/06/2026]. See the Terms and Conditions (https://onlinelibrary.wiley.com/terms-and-conditions) on Wiley Online Library for rules of use; OA articles are governed by the applicable Creative Commons License




FIGURE 4 | Mechanistic study of CO_2 activation. (A) Photoactivity of CDs in the CO_2 cycloaddition reactions using electron and hole quenchers (reaction time: 8 h, simulated sunlight, 0.7 W cm^{-2}). (B–E) EPR spectra of CDs measured under N_2 (B), CO_2 (C), N_2/epoxide **1** (D), and CO_2/epoxide **1** (E), IL = intensity of signal under light irradiation, ID = intensity of signal under dark. (F) Photo-activation of CO_2 by electron transfer from CDs rather than photo-activation of epoxides. (G) Table showing the outcome of the control experiments for photochemical effect (simulated sunlight, 0.7 W cm^{-2}). (H) Proposed mechanism of CDs-catalyzed fixation of CO_2 with epoxide.

under irradiation of natural sunlight within 24 h. For sterically hindered epoxides containing aromatic ether groups, the reaction generated cyclic carbonates **1–4** in high yields (87%–96%). Active functional groups such as alkyls and alkenes were also well tolerated in this photothermal catalytic process and provided the corresponding products **5** and **6** in high yields (93% and 89%), respectively. For the challenging low reactivity and sterically bulky substrate styrene oxide, CDs also exhibited high catalytic reactivity, resulting in the cyclic carbonate **7** with 70% yield. In addition, enantiopure epoxide could be smoothly transformed to the corresponding cyclic carbonate (*S*)-**1** without any loss of enantiomeric excess (e.e. > 99%), indicating a selective ring opening at the terminal position of the epoxide (Figure S29). A functionalized bisepoxide substrate was amenable to the CDs catalyst as well, affording bis-cyclic carbonate **8** in 92% yield, which can be used as an important building block for further synthesis of polymers such as polyurethanes and polycarbonates. Remarkably, photo-induced activation was observed for all these cases. Using the thermal conditions (oil bath) at the same system temperature as for the photothermal conditions, the yields of products **1–6** reduced by 6%–22%. Significant enhancement of photo-induced activation was observed for the formation of cyclic carbonates **7** and **8** since using thermal conditions resulted in only 14% and 7% of the target products being obtained in the absence of light irradiation, respectively. This shows that different extent of photo-induced activation can occur in reactions with different substrates.

To explore the recyclability of the CDs catalyst, the reaction for the synthesis of the useful bis-cyclic carbonate **8** was investigated under natural sunlight using 1 atm of CO_2. The yield slightly decreased from 92% to 84% after 5 cycles of recycling, but still exhibited high catalytic activity (Figure 5E). Only 1.8 wt% loss of CDs was observed after 5 cycles of reaction. Then, we increased the catalytic cycles from 5 times to 8 times, the yield of cyclic carbonate finally decreased to 71% after 8 cycles, and only 69.3 mg of CDs catalyst could be recollected (Table S3). As the CDs have a very small size (1-3 nm), the leaching of CDs during

27662098, 2026, 1, Downloaded from https://onlinelibrary.wiley.com/doi/10.1002/EXP.20250043 by CochraneChina, Wiley Online Library on [08/06/2026]. See the Terms and Conditions (https://onlinelibrary.wiley.com/terms-and-conditions) on Wiley Online Library for rules of use; OA articles are governed by the applicable Creative Commons License




FIGURE 5 | Applicability and practicability of CDs. (A) Schematic of the sunlight-catalysis device, including a Fresnel condenser, a sunlight tracking sensor, and a guidance system (optical fibers). (B) 1000 mmol scale experiment. The experiment under natural sunlight lasting for 40 h was carried during 5 days (8 h × 5). (C) Representative irradiation situation of standard reaction under natural sunlight. (D) Reaction yields for 8 and 24 h under conditions of heating, simulated sunlight, and natural sunlight. The experiment under natural sunlight lasting for 24 h was carried during 3 days (8 h × 3) in July, 2023, in Harbin, China. (E) Catalyst recycling experiments of CDs for CO_2 conversion to epoxide **8** under simulated sunlight (0.7 W cm^{-2}). (F) Substrate scope of epoxides in photothermal (sunlight) and thermal catalysis (oil bath, the reaction temperature is consistent with that of photothermal reaction). All the photothermal reactions were conducted using home-made device under natural sunlight, and the system temperature for different substrates varied from 97 to 103°C.

the recycle process is unavoidable. Moreover, recovered CDs after 5 and 8 cycles were characterized by FT-IR, XRD, TEM, Raman, and ^{1}H NMR (Figures S30–S34). The result shows that no apparent structural degradation was found, indicating the CDs have structural-stable properties in this reaction conditions. Moreover, XPS of CDs after 5 and 8 cycles shows that the element content of C, N, and O has obvious changes, and the high resolution XPS spectra for elements C, O, and N which correspond to functional groups of catalytic sites (—OH, pyridinic N, pyrrolic N, and graphitic N) also exhibits obvious changes (Figure S35), indicating that changes occurred during the cycles for surface polar groups of CDs. Despite these changes for surface groups of CDs, the CDs could still exhibit good catalytic performance (Table S3). Therefore, the mass loss during CDs recovery and partial degradation of the surface polar groups could affect the partial loss of activity of CDs, this should be taken into consideration and indeed a great challenge in industrial applications. Moreover, the photothermal effect and catalytic activity of the CDs were also evaluated on a large scale to determine the practicability of this photocatalyst. The reaction could be carried out on a 1000 mmol scale to yield 176.98 g of cyclic carbonate **1** with a high yield of 85% (Figure 5B), confirming that this method has great potential for the industrial scale synthesis of cyclic carbonates from epoxides and CO_2 due to the simple, mild, and energy-saving process.

27662098, 2026, 1, Downloaded from https://onlinelibrary.wiley.com/doi/10.1002/EXP.20250043 by CochraneChina, Wiley Online Library on [08/06/2026]. See the Terms and Conditions (https://onlinelibrary.wiley.com/terms-and-conditions) on Wiley Online Library for rules of use; OA articles are governed by the applicable Creative Commons License

We notice that only few examples of photothermal catalysts were reported for this transformation such as metal carbides [25], metal/phthalocyanine hybrids [31], metal/covalent-organic frameworks [58, 59], metal-organic frameworks [60], metal/carbon nanosheets [61], metallic oxides/organic ligands [62], and porous biochar [56, 63]. However, all these catalysts themselves showed inert or poor catalytic activity in the absence of the co-catalyst, metal, or halogen; they also had to be prepared using multiple and complex procedures (Table S4). In contrast, the CDs catalyst studied here exhibited excellent catalytic activity for both CO_2 and epoxide activation, catalyzing the cycloaddition reaction without any solvent, metal, halogen, and co-catalyst (see Table S5 for comparison with references). Notably, the simple and green preparation of CDs by a one-pot hydrothermal synthesis in H_2O shows great superiority in both fabrication process and catalytic applications comparing to previous carbon-based catalysts (Table S6).

3 | CONCLUSION

In summary, we have developed CDs as a photothermal catalyst for the fixation of CO_2 to cyclic carbonates. The carbon cores of the CDs generated thermal energy and electrons upon solar irradiation. The as-generated electrons and N-sites activated the inert CO_2. Meanwhile, epoxides were efficiently activated by surface hydroxyl and carboxylic groups of the CDs through hydrogen-bonding interactions. Activated CO_2 and epoxides efficiently reacted at solar thermal-induced high temperatures. Conquering the problems associated with previous photocatalysts, CDs were able to efficiently catalyze the reaction without any co-catalyst under natural solar irradiation, and were suitable for producing 8 different cyclic carbonates from different epoxides. Considering its low energy consumption and low cost, CDs photocatalysts are promising candidates for the practical industrial scale production of cyclic carbonates.

4 | EXPERIMENTAL SECTION

4.1 | Materials Preparations and Characterizations

All chemicals were purchased from commercial sources and used without further purification, unless otherwise noted. Gallic acid (GA, Aladdin), polyethylenimine (PEI, branched, average Mw~800 by LS, Macklin), pyrogallic acid (Aladdin), melamine (Aladdin), urea (Aladdin), benzyl glycidy ether (TCI, 97.0%), glycidyl phenyl ether (Aladdin, 99.0%), glycidyl 2-methylphenyl ether (Aladdin, 90.0%), furfuryl glycidyl ether (Aladdin, 96.0%), glycidyl propargyl ether (Aladdin, 90.0%), allyl glycidyl ether (Aladdin, 99%), styrene oxide (Aladdin, 98.0%), (*R*)-benzyl glycidyl ether (Adamas, 98%), 2,2-bis(4-glycidyloxyphenyl)propane (TCI, 85%), *N*,*N*-dimethylformamide (DMF, Aladdin, 99.9%), 2,2,2-trifluoro-*N*,*N*-dimethylacetamide (Bidepharm, 98%), chloroform-*d* ($CDCl_3$, Macklin), (trimethylsilyl)diazomethane (Aladdin), benzaldehyde (Aladdin), ultra-dry ethanol (Aladdin), and acetic anhydride (Aladdin). CO_2 was supplied from Ha Qinghua Gas Technology Co., Ltd with a purity of >99.5%. N_2 was supplied from Ha Qinghua Gas Technology Co., Ltd with a purity of >99.999%.

Reactions were monitored by thin-layer chromatography (TLC) carried out on 25 mm silica gel plates. Visualization was performed with a UV-lamp (254 nm) or $KMnO_4$ solution. Flash column chromatography was performed on silica gel (particle size 230–400 mesh, purchased from Canada) and eluted with petroleum ether/ethyl acetate. ^1H NMR spectra were recorded on Bruker-500 MHz spectrometer. The chemical shifts (δ) are given in parts per million relative to $CDCl_3$ (7.26 ppm for ^1H) or TMS (0 ppm for ^1H). The transmission electron microscopy (TEM) and high-resolution TEM (HRTEM) images were acquired on JEOL JEM-2100 instrument, simple preparation of CDs is 10 mg mL^{-1} in H_2O. X-ray diffraction (XRD) patterns were collected on the Shimadzu XRD-6100 powder diffractometer. Raman spectra were recorded using a LabRAM HR Evolution confocal Raman microscope (Horiba, ltd., Kyoto, Japan). Fourier transform infrared spectrometric (FT-IR) analysis of samples were recorded with a PerkinElmer Frontier FT-IR spectrometer. The chemical composition, content and state of the samples were determined by X-ray photoelectron spectroscopy (XPS, Thermo Scientific K-Alpha). UV–vis–NIR absorption spectra were measured on Shimadzu UV-3600i Plus. Electron paramagnetic resonance (EPR) analysis was conducted on a Bruker A300. The CEL-S500/350 Xenon lamp (purchased from Beijing China Education AuLight Technology (CEAuLight) Co., Ltd. www.litcatal.com) with reflector and AM1.5 filter simulates sunlight.

4.2 | Synthesis of CDs

All the carbon dots (CDs) were synthesized according to the following procedure: GA (85.06 mg, 0.5 mmol) and PEI (400 mg, 0.5 mmol) were dissolved in ultra pure water (30 mL) and mixed uniformly. A reactor containing the mixed solution was placed in an oven at 180°C for 8 h and then allowed to cool to room temperature naturally. The mixture was filtered through a 0.22 μm syringe filter after centrifugation followed by a dialysis through a 1000 Da dialysis bag. The purified solution was dried in an oven to give the CDs (310 mg, 64 wt% yield). The CDs prepared from GA and PEI in the ratios of 4:1, 2:1, 1:1 and 1:2 were named as 4-CDs, 2-CDs, CDs, and 0.5-CDs, respectively. The CDs prepared from GA and urea (1:1), and from GA and melamine (1:1) were named as U-CDs and M-CDs, respectively. The PEI-CDs and GA-CDs were prepared using sole PEI and GA, respectively.

4.3 | CDs-Catalyzed Reaction of CO_2 With Epoxides

For reaction conditions screening, epoxide **1** (821 mg, 5 mmol, 1 equiv.) and CDs (41 mg, 5 wt%) were weighted into a 25 mL reaction tube, followed by charging with CO_2. The reaction mixture was stirred under 1 atm of CO_2 atmosphere (balloon) and irradiation with 0.7 W cm^{-2} simulated sunlight. The reaction was monitored by TLC. After the reaction was completed, the residue was purified by column chromatography on silica gel with a gradient eluent of petroleum ether/ethyl acetate to afford the desired product. For substrate screening, the same procedure was conducted using sunlight. CO_2 was provided by a balloon filled with pure CO_2 gas and the distance between light outlet and reaction tube was ~1 cm.

27662098, 2026, 1, Downloaded from https://onlinelibrary.wiley.com/doi/10.1002/EXP.20250043 by CochraneChina, Wiley Online Library on [08/06/2026]. See the Terms and Conditions (https://onlinelibrary.wiley.com/terms-and-conditions) on Wiley Online Library for rules of use; OA articles are governed by the applicable Creative Commons License

4.4 | Large-Scale Reaction of CO_2 With Epoxide

Epoxide **1** (164.2 g, 1000 mmol) and CDs (8.2 g, 5 wt%) were weighted into a 250 mL flask, followed by charging with CO_2. The reaction mixture was stirred for 5 days (8 h × 5) under 1 atm of CO_2 atmosphere (balloon) and irradiation of sunlight. After the reaction was completed, ethyl acetate (500 mL) was added and the mixture filtrated through a short pad of silica gel. The residue was purified by column chromatography on silica gel with a gradient eluent of petroleum ether/ethyl acetate to afford the desired product **1** (183.2 g, 88% yield).

4.5 | Recycling Experiments of CDs for CO_2 Conversion

Epoxide **8** (1.702 g, 5 mmol, 1 equiv.) and CDs (82 mg) were weighted into a 25 mL reaction tube, followed by charging with CO_2. The reaction mixture was stirred under 1 atm of CO_2 atmosphere (balloon) and irradiation of simulated sunlight (0.7 W cm^{-2}). After the reaction was completed, ethyl acetate (10 mL) was added into the mixture. The CDs sediment was formed after a 30 min standing and the supernatant liquid (cyclic carbonate) was collected with a dropper carefully. The CDs sediment was washed with EA for 3 times and the dried and reused for the next cycle. The EA solution was collected and concentrated under vacuum to afford the cyclic carbonate **8**.

4.6 | Procedure for the Protection of Surface Groups of CDs

For protection of carboxyl acid, to a 10 mL oven-dried sealed tube containing a magnetic stir bar, CDs (200 mg) was added in the mixture of dichloromethane (4 mL) and methanol (4 mL). After that, (trimethylsilyl)diazomethane (79.9 mg, 0.7 mmol) was added to the mixture dropwise, and the mixture was stirred at room temperature for 12 h. After the reaction was completed, the solvent was removed under vacuum and the residue was washed with EA 3 times to remove the residual small molecules. The residue was dried to provide the methylated Me-CDs (202 mg).

For protection of amino group: To a 50 mL oven-dried sealed tube containing a magnetic stir bar, CDs (200 mg) and 4-fluorobenzaldehyde (124.1 mg, 1 mmol) were added in anhydrous ethanol (10 mL) and stirred at room temperature for 72 h. After the reaction was completed, the solvent was removed under vacuum and the residue was washed with EA 3 times to remove the residual 4-fluorobenzaldehyde. The residue was dried to provide the protected Ar-CDs (218 mg).

For protection of hydroxyl group: To a 50 mL oven-dried sealed tube containing a magnetic stir bar, CDs (200 mg) and acetic anhydride (51 mg, 0.5 mmol) were added in the anhydrous dichloromethane (8 mL) and stirred at room temperature for 12 h. After the reaction was completed, the solvent was removed under vacuum and the residue was washed with EA 3 times to remove the residual small molecules. The residue was dried to provide the acetylated Ac-CDs (196 mg).

Author Contributions

Z.C. B.T., S.L., and T.D.J. conceived the work and designed the experiments. R.W., H.G., T.Z., X.C., and M.G. were primarily responsible for the experiments. R.W., S.L., S.L., J.L. B.T., B.S., A.L.R., T.D.J., and Z.C. prepared the paper. All the authors contributed to the data analysis.

Acknowledgments

We thank the National Natural Science Foundation of China (22378056, 32171716 and 32271795), the Natural Science Funding of Heilong Jiang province for Excellent Young Scholar (YQ2022C004), and the Fundamental Research Funds for the Central Universities (2572022BB01, 2572022CG02 and 2572023CT06) for financial support. Tony D. James thanks the University of Bath and the Open Research Fund of the School of Chemistry and Chemical Engineering, Henan Normal University (2020ZD01) for support. Andrey L. Rogach acknowledges financial support from the Global Experts project funded by the Moravian-Silesian Region and VSB-TUO (contract 00734/2023/RRC).

Conflicts of Interest

The authors declare no competing interests.

Data Availability Statement

The data that support the findings of this study are available from the corresponding author upon reasonable request.

References

1. A. J. Kamphuis, F. Picchioni, and P. P. Pescarmona, "CO_2 -Fixation Into Cyclic and Polymeric Carbonates: Principles and Applications," *Green Chemistry* 21 (2019): 406–448, https://doi.org/10.1039/C8GC03086C.

2. B. Schafner, F. Schafner, S. P. Verevkin, and A. Borner, "Organic Carbonates as Solvents in Synthesis and Catalysis," *Chemical Reviews* 110 (2010): 4554–4581, https://doi.org/10.1021/cr900393d.

3. W. Guo, J. E. Gómez, À. Cristòfol, J. Xie, and A. W. Kleij, "Catalytic Transformations of Functionalized Cyclic Organic Carbonates," *Angewandte Chemie International Edition* 57 (2018): 13735–13747, https://doi.org/10.1002/anie.201805009.

4. Q. Liu, L. Wu, R. Jackstell, and M. Beller, "Using Carbon Dioxide as a Building Block in Organic Synthesis," *Nature Communications* 6 (2015): 5933, https://doi.org/10.1038/ncomms6933.

5. W.-H. Wang, Y. Himeda, J. T. Muckerman, G. F. Manbeck, and E. Fujita, "CO_2 Hydrogenation to Formate and Methanol as an Alternative to Photo- and Electrochemical CO_2 Reduction," *Chemical Reviews* 115 (2015): 12936–12973, https://doi.org/10.1021/acs.chemrev.5b00197.

6. W. Wang, S. Wang, X. Ma, and J. Gong, "Recent Advances in Catalytic Hydrogenation of Carbon Dioxide," *Chemical Society Reviews* 40 (2011): 3703, https://doi.org/10.1039/c1cs15008a.

7. J. Artz, T. E. Muller, K. Thenert, et al., "Sustainable Conversion of Carbon Dioxide: An Integrated Review of Catalysis and Life Cycle Assessment," *Chemical Reviews* 118 (2018): 434–504, https://doi.org/10.1021/acs.chemrev.7b00435.

8. L. Guo, K. J. Lamb, and M. North, "Recent Developments in Organocatalysed Transformations of Epoxides and Carbon Dioxide into Cyclic Carbonates," *Green Chemistry* 23 (2021): 77–118, https://doi.org/10.1039/D0GC03465G.

9. B.-H. Xu, J.-Q. Wang, J. Sun, et al., "Fixation of CO_2 into Cyclic Carbonates Catalyzed by Ionic Liquids: A Multi-Scale Approach," *Green Chemistry* 17 (2015): 108–122, https://doi.org/10.1039/C4GC01754D.

10. A. Decortes, A. M. Castilla, and A. W. Kleij, "Salen-Complex-Mediated Formation of Cyclic Carbonates by Cycloaddition of CO_2 to Epoxides,"

27662098, 2026, 1, Downloaded from https://onlinelibrary.wiley.com/doi/10.1002/EXP.20250043 by CochraneChina, Wiley Online Library on [08/06/2026]. See the Terms and Conditions (https://onlinelibrary.wiley.com/terms-and-conditions) on Wiley Online Library for rules of use; OA articles are governed by the applicable Creative Commons License

Angewandte Chemie International Edition 49 (2010): 9822–9837, https://doi.org/10.1002/anie.201002087.

11. R. Huang, J. Rintjema, J. González-Fabra, et al., "Deciphering Key Intermediates in the Transformation of Carbon Dioxide into Heterocyclic Products," *Nature Catalysis* 2 (2019): 62–70, https://doi.org/10.1038/s41929-018-0189-z.

12. J. O. Kroll, J. Kothandaraman, K. Grubel, and D. J. Heldebrant, "Integrated Approach to CO_2 Capture and Conversion to Cyclic Carbonates Under Solvent- and Additive-Free Conditions Utilizing the CO_2 Capture Solvent EEMPA," *Energy & Fuels* 38 (2024): 7959–7965, https://doi.org/10.1021/acs.energyfuels.3c04993.

13. W. Zhou, Q. W. Deng, G. Q. Ren, et al., "Enhanced Carbon Dioxide Conversion at Ambient Conditions via a Pore Enrichment Effect," *Nature Communications* 11 (2020): 4481, https://doi.org/10.1038/s41467-020-18154-9.

14. Y. Zhi, P. Shao, X. Feng, et al., "Covalent Organic Frameworks: Efficient, Metal-Free, Heterogeneous Organocatalysts for Chemical Fixation of CO_2 Under Mild Conditions," *Journal of Materials Chemistry A* 6 (2018): 374–382, https://doi.org/10.1039/C7TA08629F.

15. T. K. Pal, D. De, and P. K. Bharadwaj, "Metal–Organic Frameworks for the Chemical Fixation of CO_2 Into Cyclic Carbonates," *Coordination Chemistry Reviews* 408 (2020): 213173, https://doi.org/10.1016/j.ccr.2019.213173.

16. J. W. Maina, C. Pozo-Gonzalo, L. Kong, J. Schütz, M. Hill, and L. F. Dumée, "Metal Organic Framework Based Catalysts for CO_2 Conversion," *Materials Horizons* 4 (2017): 345.

17. M. Zhu and M. A. Carreon, "Porous Crystals as Active Catalysts for the Synthesis of Cyclic Carbonates," *Journal of Applied Polymer Science* 131 (2014): 39738, https://doi.org/10.1002/app.39738.

18. Y. Xie, T.-T. Wang, X.-H. Liu, K. Zou, and W.-Q. Deng, "Capture and Conversion of CO_2 at Ambient Conditions by a Conjugated Microporous Polymer," *Nature Communications* 4 (2013): 1960, https://doi.org/10.1038/ncomms2960.

19. K. S. Song, P. W. Fritz, and A. Coskun, "Porous Organic Polymers for CO_2 Capture, Separation and Conversion," *Chemical Society Reviews* 51 (2022): 9831–9852, https://doi.org/10.1039/D2CS00727D.

20. A. Helal, M. Fettouhi, S. M. Alqahtani, Y. Umar, S. Khan, and M. A. Sanhoob, "Nitrogen-Rich Barium–Organic Framework for Capture and Cocatalysts Free Chemical Fixation of CO_2 via Cyclic Carbonates and Oxazolidinones," *ACS Applied Materials & Interfaces* 17 (2025): 6271–6281, https://doi.org/10.1021/acsami.4c18062.

21. P. Mikšovsky, K. Rauchenwald, S. Naghdi, et al., "Silicon Oxycarbide (SiOC)-Supported Ionic Liquids: Heterogeneous Catalysts for Cyclic Carbonate Formation," *ACS Sustainable Chemistry & Engineering* 12 (2024): 1455–1467, https://doi.org/10.1021/acssuschemeng.3c05569.

22. M. H. Alenazi, A. Helal, M. Y. Khan, et al., "Covalent Organic Frameworks (COFs) for CO_2 Utilizations," *Carbon Capture Science & Technology* 14 (2025): 100365.

23. A. Helal, M. H. Zahir, A. Albadrani, and M. M. Ekhwan, "Triazole Appended Metal–Organic Framework for CO_2 Fixation as Cyclic Carbonates Under Solvent-Free Ambient Conditions," *Catalysis Letters* 153 (2023): 2883–2891, https://doi.org/10.1007/s10562-022-04213-x.

24. G. Zhai, Y. Liu, Y. Mao, et al., "Improved Photocatalytic CO_2 and Epoxides Cycloaddition via the Synergistic Effect of Lewis Acidity and Charge Separation over Zn Modified UiO-bpydc," *Applied Catalysis B: Environment and Energy* 301 (2022): 120793, https://doi.org/10.1016/j.apcatb.2021.120793.

25. Q. Guo, S. G. Xia, X. B. Li, et al., "Flower-Like Cobalt Carbide for Efficient Carbon Dioxide Conversion," *Chemical Communications* 56 (2020): 7849–7852, https://doi.org/10.1039/D0CC01091J.

26. Q. Yang, H. Peng, Q. Zhang, et al., "Atomically Dispersed High-Density Al–N_4 Sites in Porous Carbon for Efficient Photodriven CO_2 Cycloaddition," *Advanced Materials* 33 (2021): 2103186, https://doi.org/10.1002/adma.202103186.

27. X. Chen, M. Wei, A. Yang, et al., "Near-Infrared Photothermal Catalysis for Enhanced Conversion of Carbon Dioxide under Mild Conditions," *ACS Applied Materials & Interfaces* 14 (2022): 5194–5202, https://doi.org/10.1021/acsami.1c18889.

28. L. P. Zhang, X. W. Tu, Y. Chen, et al., "Photothermal Catalysis Without Solvent for Fixing CO_2 to Cyclic Carbonate," *Molecular Catalysis* 538 (2023): 112971.

29. L. Gong, J. Sun, Y. Liu, and G. Yang, "Photoinduced Synergistic Catalysis on Zn Single-Atom-Loaded Hierarchical Porous Carbon for Highly Efficient CO_2 Cycloaddition Conversion," *Journal of Materials Chemistry A* 9 (2021): 21689–21694, https://doi.org/10.1039/D1TA06159C.

30. R. Cheng, A. Wang, S. Sang, H. Liang, S. Liu, and P. Tsiakaras, "Photocatalytic CO_2 Cycloaddition over Highly Efficient $W_{18}O_{49}$-Based Composites: An Economic and Ecofriendly Choice," *Chemical Engineering Journal* 466 (2023): 142982, https://doi.org/10.1016/j.cej.2023.142982.

31. P. K. Prajapati, A. Kumar, and S. L. Jain, "First Photocatalytic Synthesis of Cyclic Carbonates from CO_2 and Epoxides Using CoPc/TiO_2 Hybrid Under Mild Conditions," *ACS Sustainable Chemistry & Engineering* 6 (2018): 7799–7809, https://doi.org/10.1021/acssuschemeng.8b00755.

32. N. Das, R. Paul, S. Biswas, et al., "Photo-Responsive Signatures in a Porous Organic Polymer Enable Visible Light-Driven CO_2 Photofixation," *ACS Sustainable Chemistry & Engineering* 11 (2023): 2066–2078, https://doi.org/10.1021/acssuschemeng.2c04428.

33. M. Bakiro, S. Hussein Ahmed, and A. Alzamly, "Efficient Visible-Light Photocatalytic Cycloaddition of CO_2 and Propylene Oxide Using Reduced Graphene Oxide Supported $BiNbO_4$," *ACS Sustainable Chemistry & Engineering* 8 (2020): 12072–12079, https://doi.org/10.1021/acssuschemeng.0c03363.

34. C.-L. Tan, M.-Y. Qi, Z.-R. Tang, and Y.-J. Xu, "Isolated Single-Atom Cobalt in the $ZnIn_2S_4$ Monolayer With Exposed Zn Sites for CO_2 Photofixation," *ACS Catalysis* 13 (2023): 8317–8329, https://doi.org/10.1021/acscatal.3c00992.

35. A. Said, G. Zhang, C. Liu, et al., "A Butterfly-Like Lead-Doped Titanium-Oxide Compound With High Performance in Photocatalytic Cycloaddition of CO_2 to Epoxide," *Dalton Transactions* 52 (2023): 2392–2403, https://doi.org/10.1039/D2DT03990G.

36. X. Xu, R. Ray, Y. Gu, et al., "Electrophoretic Analysis and Purification of Fluorescent Single-Walled Carbon Nanotube Fragments," *Journal of the American Chemical Society* 126 (2024): 12736–12737, https://doi.org/10.1021/ja040082h.

37. K. Hola, Y. Zhang, Y. Wang, E. P. Giannelis, R. Zboril, and A. L. Rogach, "Carbon Dots—Emerging Light Emitters for Bioimaging, Cancer Therapy and Optoelectronics," *Nano Today* 9 (2014): 590–603, https://doi.org/10.1016/j.nantod.2014.09.004.

38. L. Đorđević, F. Arcudi, M. Cacioppo, and M. Prato, "multifunctional Chemical Toolbox to Engineer Carbon Dots for Biomedical and Energy Applications," *Nature Nanotechnology* 17 (2022): 112–130.

39. G. Ragazzon, A. Cadranel, E. V. Ushakova, et al., "Optical Processes in Carbon Nanocolloids," *Chemistry* 7 (2021): 606–628, https://doi.org/10.1016/j.chempr.2020.11.012.

40. C. Rosso, G. Filippini, and M. Prato, "Carbon Dots as Nano-Organocatalysts for Synthetic Applications," *ACS Catalysis* 10 (2020): 8090–8105, https://doi.org/10.1021/acscatal.0c01989.

41. B. Jana, Y. Reva, T. Scharl, V. Strauss, A. Cadranel, and D. M. Guldi, "Carbon Nanodots for All-in-One Photocatalytic Hydrogen Generation," *Journal of the American Chemical Society* 143 (2021): 20122–20132, https://doi.org/10.1021/jacs.1c07049.

42. J. Lu, Y. Shi, Z. Chen, et al., "Photothermal Effect of Carbon Dots for Boosted Photothermal-Assisted Photocatalytic Water/Seawater Splitting into Hydrogen," *Chemical Engineering Journal* 453 (2023): 139834, https://doi.org/10.1016/j.cej.2022.139834.

27662098, 2026, 1, Downloaded from https://onlinelibrary.wiley.com/doi/10.1002/EXP.20250043 by CochraneChina, Wiley Online Library on [08/06/2026]. See the Terms and Conditions (https://onlinelibrary.wiley.com/terms-and-conditions) on Wiley Online Library for rules of use; OA articles are governed by the applicable Creative Commons License

43. K. Wang, R. Jiang, T. Peng, X. Chen, W. Dai, and X. Fu, "Modeling the Effect of Cu Doped TiO_2 with Carbon Dots on CO_2 Methanation by H_2O in a Photo-Thermal System," *Applied Catalysis B: Environment and Energy* 256 (2019): 117780, https://doi.org/10.1016/j.apcatb.2019.117780.

44. J. H. Zhang, J. C. Liu, X. Y. Wang, et al., "Construction of Z-Scheme Tungsten Trioxide Nanosheets-Nitrogen-Doped Carbon Dots Composites for the Enhanced Photothermal Synergistic Catalytic Oxidation of Cyclohexane," *Applied Catalysis B: Environment and Energy* 259 (2019): 118063.

45. Q. Cheng, Z. Wang, X. Wang, J. Li, Y. Li, and G. Zhang, "A Novel $Cu_{1.5}Mn_{1.5}O_4$ Photothermal Catalyst With Boosted Surface Lattice Oxygen Activation for Efficiently Photothermal Mineralization of Toluene," *Nano Research* 16 (2023): 2133–2141, https://doi.org/10.1007/s12274-022-4946-6.

46. X. Wang, X. Feng, J. Liu, et al., "Photo-Thermo Catalytic Selective Oxidation of Cyclohexane by In-Situ Prepared Nonstoichiometric Molybdenum Oxide and Silver-Palladium Alloy Composite," *Journal of Colloid and Interface Science* 607 (2022): 954–966, https://doi.org/10.1016/j.jcis.2021.09.058.

47. L. H. Kugelmass, C. Tagnon, and E. E. Stache, "Photothermal Mediated Chemical Recycling to Monomers via Carbon Quantum Dots," *Journal of the American Chemical Society* 145 (2023): 16090–16097, https://doi.org/10.1021/jacs.3c04448.

48. D. S. Achilleos, W. Yang, H. Kasap, et al., "Solar Reforming of Biomass With Homogeneous Carbon Dots," *Angewandte Chemie, International Edition* 59 (2020): 18184–18188, https://doi.org/10.1002/anie.202008217.

49. Z. Li, H. Lei, A. Kan, H. Xie, and W. Yu, "Photothermal Applications Based on Graphene and Its Derivatives: A State-of-the-Art Review," *Energy* 216 (2021): 119262, https://doi.org/10.1016/j.energy.2020.119262.

50. S. Balou, P. Shandilya, and A. Priye, "Carbon Dots for Photothermal Applications," *Frontiers in Chemistry* 10 (2022): 1023602, https://doi.org/10.3389/fchem.2022.1023602.

51. C. Claver, M. B. Yeamin, M. Reguero, and A. M. Masdeu-Bulto, "Recent Advances in the Use of Catalysts Based on Natural Products for the Conversion of CO_2 Into Cyclic Carbonates," *Green Chemistry* 22 (2020): 7665–7706, https://doi.org/10.1039/D0GC01870H.

52. K. R. Roshan, B. M. Kim, A. C. Kathalikkattil, J. Tharun, Y. S. Won, and D. W. Park, "The Unprecedented Catalytic Activity of Alkanolamine CO_2 Scrubbers in the Cycloaddition of CO_2 and Oxiranes: A DFT Endorsed Study," *Chemical Communications* 50 (2014): 13664–13667, https://doi.org/10.1039/C4CC04195J.

53. M. Alves, B. Grignard, R. Méreau, C. Jerome, T. Tassaing, and C. Detrembleur, "Organocatalyzed Coupling of Carbon Dioxide with Epoxides for the Synthesis of Cyclic Carbonates: Catalyst Design and Mechanistic Studies," *Catalysis Science & Technology* 7 (2017): 2651–2684, https://doi.org/10.1039/C7CY00438A.

54. J. Sheng, Y. He, J. Li, et al., "Identification of Halogen-Associated Active Sites on Bismuth-Based Perovskite Quantum Dots for Efficient and Selective CO_2-to-CO Photoreduction," *ACS Nano* 14 (2020): 13103–13114, https://doi.org/10.1021/acsnano.0c04659.

55. I. M. Garazade, R. K. Gupta, K. Singh, et al., "Insights Into the Catalytic Application of Coordinated Metal Complexes in CO_2 Conversion via Cycloaddition," *Journal of Molecular Structure* 1337 (2025): 142200, https://doi.org/10.1016/j.molstruc.2025.142200.

56. Y. Wang, H. Liu, Q. Shi, et al., "Single-Atom Titanium on Mesoporous Nitrogen, Oxygen-Doped Carbon for Efficient Photo-Thermal Catalytic CO_2 Cycloaddition by a Radical Mechanism," *Angewandte Chemie, International Edition* 63 (2024): e202404911, https://doi.org/10.1002/anie.202404911.

57. F. A. Villamena, E. J. Locigno, A. Rockenbauer, C. M. Hadad, and J. L. Zweier, "Theoretical and Experimental Studies of the Spin Trapping of Inorganic Radicals by 5,5-Dimethyl-1-Pyrroline N-Oxide (DMPO). 1. Carbon Dioxide Radical Anion," *Journal of Physical Chemistry A* 110 (2006): 13253–13258, https://doi.org/10.1021/jp064892m.

58. L.-G. Ding, B.-J. Yao, W.-X. Wu, et al., "Metalloporphyrin and Ionic Liquid-Functionalized Covalent Organic Frameworks for Catalytic CO_2 Cycloaddition via Visible-Light-Induced Photothermal Conversion," *Inorganic Chemistry* 60 (2021): 12591–12601, https://doi.org/10.1021/acs.inorgchem.1c01975.

59. Z. Wang, T. Wang, Y. Zhao, Q. Ye, and P. He, "Photothermal CO_2 Conversion to Cyclic Carbonate Over Titanium-Substituted Polyoxometalate Within Covalent Organic Frameworks," *Journal of Catalysis* 442 (2025): 115908, https://doi.org/10.1016/j.jcat.2024.115908.

60. H. Zhang, G. Zhai, L. Lei, et al., "Photo-Induced Photo-Thermal Synergy Effect Leading to Efficient CO_2 Cycloaddition with Epoxide over a Fe-Based Metal Organic Framework," *Journal of Colloid & Interface Science* 625 (2022): 33–40, https://doi.org/10.1016/j.jcis.2022.05.146.

61. Y. Liu, Y. Chen, Y. Liu, et al., "Zn and N Co-Doped Porous Carbon Nanosheets for Photothermally-Driven CO_2 Cycloaddition," *Journal of Catalysis* 407 (2022): 65–76, https://doi.org/10.1016/j.jcat.2022.01.016.

62. L. P. Zhang, X. W. Tu, Y. T. Chen, et al., "Photothermal Catalysis Without Solvent for Fixing CO2 to Cyclic Carbonate," *Molecular Catalysis* 538 (2023): 112971–112979.

63. W. Rong, M. Ding, Y. Wang, S. Kong, and J. Yao, "Porous Biochar with a Tubular Structure for Photothermal CO_2 Cycloaddition: One-Step Doping Versus Two-Step Doping," *Separation and Purification Technology* 353 (2025): 128427, https://doi.org/10.1016/j.seppur.2024.128427.

Supporting Information

Additional supporting information can be found online in the Supporting Information section.

Supporting File 1: exp270130-sup-001-SuppMat.pdf.

27662098, 2026, 1, Downloaded from https://onlinelibrary.wiley.com/doi/10.1002/EXP.20250043 by CochraneChina, Wiley Online Library on [08/06/2026]. See the Terms and Conditions (https://onlinelibrary.wiley.com/terms-and-conditions) on Wiley Online Library for rules of use; OA articles are governed by the applicable Creative Commons License